WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL



Machine Id **LIEBHERR R926K-LC 56729**

Right Final Drive

LIEBHERR GEAR BASIC 90 LS	(GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Confirm the source of the lubricant being utilized for top-up/fill. Resample at the next service interval to monitor.	Sample Number		Client Info		LH		
	Sample Date		Client Info		06 May 2024		
	Machine Age	hrs	Client Info		512		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185(m)	>500	142		
	Chromium	ppm	ASTM D5185(m)	>10	2		
	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		<1		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>25	2		
	Lead	ppm	ASTM D5185(m)	>25	0		
	Copper	ppm	ASTM D5185(m)		<1		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	VLITE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185(m)	>75	7		
	Potassium	ppm	ASTM D5185(m)	>20	7		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor Emulsified Water	scalar	Visual* Visual*	NORML >0.2	NORML NEG		
		scalar	VISUAI	>0.2			
FLUID CONDITION Additive levels indicate the addition of a different brand, or type of oil. The condition of the oil is acceptable for the time in service.	Sodium	ppm	ASTM D5185(m)		7		
	Boron	ppm	ASTM D5185(m)	0	4		
	Barium	ppm	ASTM D5185(m)		16		
	Molybdenum	ppm	ASTM D5185(m)	0	0		
	Manganese	ppm	ASTM D5185(m)		2		
	Magnesium	ppm	ASTM D5185(m)		1		
	Calcium	ppm	ASTM D5185(m)		21		
	Phosphorus	ppm	, ,	2143	1137		
	Zinc	ppm	ASTM D5185(m)	<1	22		
	Sulfur	ppm	ASTM D5185(m)		24248		
Report Id: ROLBAI [WCAMIS] 02634683 (Generated: 05/10/2024 15:48:45) Rev: 1	Visc @ 40°C	cSt	ASTM D7279(m)	170	203 Subr	 nitted By: Br	runo Savard





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : LH : 02634683 Unique Number : 5775836 Test Package : MOB 1

Received **Tested**

: 10 May 2024 : 10 May 2024

Diagnosed : 10 May 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

ROLAND MUNGER

2665 AVENUE DU LABRADOR BAIE COMEAU, QC CA G4Z 3B9

Contact: Roland Munger

T: (661)015-6791 F: