



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
122
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON UHP 5W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PC0078282	PC0078525	PC0077627
Sample Date		Client Info		03 May 2024	25 Jan 2024	16 Oct 2023
Machine Age	kms	Client Info		556068	522737	493683
Oil Age	kms	Client Info		30000	30000	30000
Filter Age	kms	Client Info		30000	30000	30000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>165	11	11	11
Chromium	ppm	ASTM D5185(m)	>5	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>4	0	<1	0
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	1	2	1
Lead	ppm	ASTM D5185(m)	>150	0	<1	1
Copper	ppm	ASTM D5185(m)	>90	2	<1	1
Tin	ppm	ASTM D5185(m)	>5	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>35	5	6	6
Potassium	ppm	ASTM D5185(m)	>20	<1	1	0
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>7.5	0.4	0.4	0.4
Nitration	Abs/cm	ASTM D7624*	>20	11.1	11.0	10.4
Sulfation	Abs/.1mm	ASTM D7415*	>30	22.6	22.5	22.2
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		4	5	4
Boron	ppm	ASTM D5185(m)	65	34	30	24
Barium	ppm	ASTM D5185(m)	0	0	0	<1
Molybdenum	ppm	ASTM D5185(m)	65	62	61	64
Manganese	ppm	ASTM D5185(m)	0	0	0	0
Magnesium	ppm	ASTM D5185(m)	1160	1124	1102	1145
Calcium	ppm	ASTM D5185(m)	820	884	875	873
Phosphorus	ppm	ASTM D5185(m)	1160	1018	1035	1021
Zinc	ppm	ASTM D5185(m)	1260	1231	1227	1230
Sulfur	ppm	ASTM D5185(m)	3000	2727	2952	2690
Oxidation	Abs/.1mm	ASTM D7414*	>25	21.0	20.8	20.1
Visc @ 40°C	cSt	ASTM D7279(m)	95.1	79.7	81.6	82.9
Visc @ 100°C	cSt	ASTM D7279(m)	14.3	12.8	13.1	13.1
Viscosity Index (VI)	Scale	ASTM D2270*	169	160	161	159



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0078282 **Received** : 13 May 2024
Lab Number : 02634879 **Tested** : 13 May 2024
Unique Number : 5776032 **Diagnosed** : 13 May 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: KV40, VI)

BEAVER BUS LINES
 339, ACHIBAULD ST
 WINNIPEG, MB
 CA R2J 0W6
 Contact: Roger Roman
 roger@beaverbus.com
 T: (204)989-7033
 F: (204)237-2645

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.