



POWER SYSTEMS
SYSTÈMES DE PUISSANCE

COOLANT REPORT

CORROSION	NORMAL
CONTAMINANTS	NORMAL
COOLANT CONDITION	NORMAL

Area
[287008]

Machine Id
GEN B
Component
Coolant

Fluid
DETROIT DIESEL POWER COOL (--- GAL)

RECOMMENDATION

The fluid is suitable for further service. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WA0018427	---	---
Sample Date		Client Info		06 May 2024	---	---
Machine Age	hrs	Client Info		0	---	---
Oil Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		N/A	---	---
Sample Status				NORMAL	---	---

CORROSION

All metal levels are normal indicating no corrosion in the cooling system.

Iron	ppm	ASTM D5185(m)	>15	<1	---	---
Aluminum	ppm	ASTM D5185(m)	>10	<1	---	---
Copper	ppm	ASTM D5185(m)	>10	0	---	---
Lead	ppm	ASTM D5185(m)	>10	0	---	---
Tin	ppm	ASTM D5185(m)	>10	0	---	---
Silver	ppm	ASTM D5185(m)	>10	<1	---	---
Zinc	ppm	ASTM D5185(m)	>10	1	---	---

CONTAMINANTS








There is no indication of any contamination in the coolant.

Calcium	ppm	ASTM D5185(m)	>100	4	---	---
Magnesium	ppm	ASTM D5185(m)	>40	1	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Coolant Appearance		Visual*	Clear	Clear	---	---

COOLANT CONDITION

The pH level of this fluid is within the acceptable limits. The reserve alkalinity of this fluid is acceptable.

Boiling Point	°C	WC Method*		107	---	---
Specific Gravity		ASTM D1298*		1.068	---	---
pH	Scale 0-14	ASTM D1287*	9.5	8.79	---	---
Nitrites	ppm	Alcan Test Kit*	500	960	---	---
Reserve Alkalinity	Scale 0-20	ASTM D1121*		3.1	---	---
Percentage Glycol	%	ASTM D3321*	50	50.8	---	---
Freezing Point	°C	ASTM D3321*	-40	-37	---	---
Carboxylate				---	---	---
Silicon	ppm	ASTM D5185(m)	150	31	---	---
Phosphorus	ppm	ASTM D5185(m)	0	46	---	---
Boron	ppm	ASTM D5185(m)	300	227	---	---
Molybdenum	ppm	ASTM D5185(m)		4	---	---
Sodium	ppm	ASTM D5185(m)		1933	---	---
Potassium	ppm	ASTM D5185(m)		85	---	---
Coolant Color		Visual*	Pink	Purple	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WA0018427 **Received** : 14 May 2024
Lab Number : 02635425 **Tested** : 14 May 2024
Unique Number : 5776578 **Diagnosed** : 15 May 2024 - Kevin Marson
Test Package : COOL (Additional Tests: GlycolType)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Wajax Power Systems
 70 Raddall Avenue
 Dartmouth, NS
 CA B3B 1T7
 Contact: Danelle Hoffman
 dhoffman@wajax.com
 T: (902)468-6200
 F: (902)468-3325