



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1516
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 5W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PC0083215	PC0083688	PC0082452
Sample Date		Client Info		14 May 2024	04 Feb 2024	31 Oct 2023
Machine Age	hrs	Client Info		6586	6046	5577
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>100	17	15	16
Chromium	ppm	ASTM D5185(m)	>20	0	0	0
Nickel	ppm	ASTM D5185(m)	>4	0	<1	<1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>3	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	5	5	5
Lead	ppm	ASTM D5185(m)	>40	0	0	<1
Copper	ppm	ASTM D5185(m)	>330	1	<1	1
Tin	ppm	ASTM D5185(m)	>15	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	7	9	12
Potassium	ppm	ASTM D5185(m)	>20	2	5	8
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>3	0.3	0.2	0.3
Nitration	Abs/cm	ASTM D7624*	>20	8.3	7.7	7.9
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.7	20.3	19.8
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>44	1	1	1
Boron	ppm	ASTM D5185(m)	250	<1	<1	<1
Barium	ppm	ASTM D5185(m)	10	0	0	<1
Molybdenum	ppm	ASTM D5185(m)	100	59	56	60
Manganese	ppm	ASTM D5185(m)		<1	0	0
Magnesium	ppm	ASTM D5185(m)	450	972	920	967
Calcium	ppm	ASTM D5185(m)	3000	1099	1186	1113
Phosphorus	ppm	ASTM D5185(m)	1150	1015	1018	997
Zinc	ppm	ASTM D5185(m)	1350	1208	1185	1191
Sulfur	ppm	ASTM D5185(m)	4250	2483	2734	2478
Oxidation	Abs/.1mm	ASTM D7414*	>25	15.4	15.8	15.4
Visc @ 40°C	cSt	ASTM D7279(m)	91	93.7	92.2	92.9
Visc @ 100°C	cSt	ASTM D7279(m)	14.4	13.7	13.8	13.9
Viscosity Index (VI)	Scale	ASTM D2270*	164	148	152	152



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC0083215
Lab Number : 02635576
Unique Number : 5776729
Test Package : MOB 1 (Additional Tests: KV40, VI)

LES ENTREPRISES MICHAUVILLE INC.
 270 RUE BRUNET
 MONT ST-HILAIRE, QC
 CA J3H 0M6
 Contact: Martin Trudel
 mtrudel@michaudville.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.