

Machine Id  
**MAINTOU NO UNIT PC0075952**  
Component  
**Rear Differential**  
Fluid  
**{not provided} (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

**WEAR**

All component wear rates are normal.











**CONTAMINATION**

There is no indication of any contamination in the oil.

**FLUID CONDITION**

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PC0075952</b>	---	---
Sample Date		Client Info		<b>14 May 2024</b>	---	---
Machine Age	hrs	Client Info		<b>2786</b>	---	---
Oil Age	hrs	Client Info		<b>0</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>N/A</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>NORMAL</b>	---	---
Iron	ppm	ASTM D5185(m)	>500	<b>27</b>	---	---
Chromium	ppm	ASTM D5185(m)	>10	<b>&lt;1</b>	---	---
Nickel	ppm	ASTM D5185(m)	>10	<b>0</b>	---	---
Titanium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Silver	ppm	ASTM D5185(m)		<b>0</b>	---	---
Aluminum	ppm	ASTM D5185(m)	>25	<b>2</b>	---	---
Lead	ppm	ASTM D5185(m)	>25	<b>0</b>	---	---
Copper	ppm	ASTM D5185(m)	>100	<b>&lt;1</b>	---	---
Tin	ppm	ASTM D5185(m)	>10	<b>0</b>	---	---
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	---	---
White Metal	scalar	Visual*	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	---	---
Silicon	ppm	ASTM D5185(m)	>75	<b>11</b>	---	---
Potassium	ppm	ASTM D5185(m)	>20	<b>2</b>	---	---
Water		WC Method	>.2	<b>NEG</b>	---	---
Silt	scalar	Visual*	NONE	<b>NONE</b>	---	---
Debris	scalar	Visual*	NONE	<b>VLITE</b>	---	---
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	---	---
Appearance	scalar	Visual*	NORML	<b>NORML</b>	---	---
Odor	scalar	Visual*	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	Visual*	>.2	<b>NEG</b>	---	---
Sodium	ppm	ASTM D5185(m)		<b>3</b>	---	---
Boron	ppm	ASTM D5185(m)		<b>136</b>	---	---
Barium	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Molybdenum	ppm	ASTM D5185(m)		<b>0</b>	---	---
Manganese	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Magnesium	ppm	ASTM D5185(m)		<b>21</b>	---	---
Calcium	ppm	ASTM D5185(m)		<b>3671</b>	---	---
Phosphorus	ppm	ASTM D5185(m)		<b>1013</b>	---	---
Zinc	ppm	ASTM D5185(m)		<b>645</b>	---	---
Sulfur	ppm	ASTM D5185(m)		<b>3278</b>	---	---
Visc @ 40°C	cSt	ASTM D7279(m)		<b>51.9</b>	---	---
Visc @ 100°C	cSt	ASTM D7279(m)		<b>8.4</b>	---	---
Viscosity Index (VI)	Scale	ASTM D2270*		<b>136</b>	---	---



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : PC0075952 **Received** : 15 May 2024  
**Lab Number** : 02635807 **Tested** : 16 May 2024  
**Unique Number** : 5776960 **Diagnosed** : 16 May 2024 - Wes Davis  
**Test Package** : MOB 1 ( Additional Tests: KV100, VI )

**J. RENE LAFOND INC**  
 3203 CHEM. CHARLES - LEONARD  
 MIRABEL, QC  
 CA J7N 2Y7  
 Contact: Service Manager  
 epoirier@jrenelafond.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

T:  
F: