



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
LIEBHERR LH50M 146771-1216
Component
Front Left Wheel Hub
Fluid
PETRO CANADA TRAXON SYNTHETIC 75W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC	---	---
Sample Date		Client Info		04 May 2024	---	---
Machine Age	hrs	Client Info		2027	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Not Changed	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>325	94	---	---
Chromium	ppm	ASTM D5185(m)	>3	<1	---	---
Nickel	ppm	ASTM D5185(m)	>2	0	---	---
Titanium	ppm	ASTM D5185(m)		0	---	---
Silver	ppm	ASTM D5185(m)		0	---	---
Aluminum	ppm	ASTM D5185(m)	>10	3	---	---
Lead	ppm	ASTM D5185(m)	>4	<1	---	---
Copper	ppm	ASTM D5185(m)	>75	22	---	---
Tin	ppm	ASTM D5185(m)	>3	0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---
White Metal	scalar	Visual*	NONE	VLITE	---	---
Yellow Metal	scalar	Visual*	NONE	NONE	---	---

CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>75	12	---	---
Potassium	ppm	ASTM D5185(m)	>20	4	---	---
Water		WC Method	>0.2	NEG	---	---
Silt	scalar	Visual*	NONE	VLITE	---	---
Debris	scalar	Visual*	NONE	NONE	---	---
Sand/Dirt	scalar	Visual*	NONE	NONE	---	---
Appearance	scalar	Visual*	NORML	NORML	---	---
Odor	scalar	Visual*	NORML	NORML	---	---
Emulsified Water	scalar	Visual*	>0.2	NEG	---	---

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		8	---	---
Boron	ppm	ASTM D5185(m)	328	56	---	---
Barium	ppm	ASTM D5185(m)	1	1	---	---
Molybdenum	ppm	ASTM D5185(m)		0	---	---
Manganese	ppm	ASTM D5185(m)		4	---	---
Magnesium	ppm	ASTM D5185(m)	1	3	---	---
Calcium	ppm	ASTM D5185(m)	7	61	---	---
Phosphorus	ppm	ASTM D5185(m)	1145	1601	---	---
Zinc	ppm	ASTM D5185(m)	3	39	---	---
Sulfur	ppm	ASTM D5185(m)	17909	23313	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	99.6	136	---	---



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC
Lab Number : 02636155
Unique Number : 5785317
Test Package : MOB 1
Received : 16 May 2024
Tested : 16 May 2024
Diagnosed : 16 May 2024 - Wes Davis

Recyclage de Metaux Integre Inc. - RMI Inc.
 1000 Route 389
 Fermont, QC
 CA G0G 1J0
 Contact: Paul Germain
 pgermain@rmi-imr.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

T:
F: