WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

ROSCO 845-0700

Diesel Engine

DIESEL ENGINE OIL SAF 15W40 (--- GAL)

DIESEL ENGINE OIL SAE 15W40 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DIESEL ENGINE OIL SAE 15W40. Please confirm.	Sample Number		Client Info		PC0088640		
	Sample Date	lawa	Client Info		08 Apr 2024		
	Machine Age	hrs	Client Info		851		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>100	7		
WEAT	Chromium	ppm	ASTM D5185(m)		0		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185(m)	>4	0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)	>3	0		
	Aluminum	ppm	ASTM D5185(m)		2		
	Lead	ppm	ASTM D5185(m)	>40	4		
	Copper	ppm	ASTM D5185(m)	>330	2		
	Tin	ppm	ASTM D5185(m)	>15	0		
	Vanadium	ppm	ASTM D5185(m)	710	0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	VLITE		
	·····						
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	5		
	Potassium	ppm	ASTM D5185(m)	>20	0		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*	>3	0		
	Nitration	Abs/cm	ASTM D7624*	>20	5.8		
	Sulfation	Abs/.1mm	ASTM D7415*	>30	18.4		
	Silt	scalar	Visual*	NONE	VLITE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
ELUD CONDITION							
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>158	1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		3		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)	100	59		
	Manganese	ppm	ASTM D5185(m)	450	0		
	Magnesium	ppm	ASTM D5185(m)		982		
	Calcium	ppm	ASTM D5185(m)	3000	1087		
	Phosphorus	ppm	ASTM D5185(m)		1017		
	Zinc	ppm	. ,	1350	1194		
	Sulfur	ppm	ASTM D5185(m)		2579		
	Oxidation	Abs/.1mm	ASTM D7414*		14.2		
	Visc @ 40°C	cSt	ASTM D7279(m)		114		
	Visc @ 100°C	cSt	ASTM D7279(m)	14.4	15.1		
	Viscosity Index (VI)	Scale	ASTM D2270*	126	137		





CALA
Leng
Americación 19991

ISO 17025:2017
Accredited

 Laboratory
 : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9

 Sample No.
 : PC0088640
 Received
 : 17 May 2024

 Lab Number
 : 02636270
 Tested
 : 17 May 2024

Accredited Laboratory Unique Number : 5785432 Diagnosed : 17 May 2024 - Wes Davis Test Package : MOB 1 (Additional Tests: KV40, VI, Visual)

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

37462A HURON ROAD CLINTON, ON CA N0M 1L0 Contact: Doug Francis dfrancis@lavis.ca T: (519)482-3694 F: (519)482-7886

LAVIS CONTRACTING