WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



Machine Id
54
Component
Diesel Engine
Fluid

SAE 5W40 ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEOGRAMIETO, THOR	Sample Number		Client Info		PC0035315		
Resample at the next service interval to monitor.	Sample Date		Client Info		14 May 2024		
	Machine Age	hrs	Client Info		3506		
	Oil Age	hrs	Client Info		250		
	Filter Age	hrs	Client Info		250		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>100	11		
	Chromium	ppm	ASTM D5185(m)	>20	0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185(m)	>2	0		
	Titanium	ppm	ASTM D5185(m)	>2	0		
	Silver	ppm	ASTM D5185(m)	>2	0		
	Aluminum	ppm	ASTM D5185(m)	>25	3		
	Lead	ppm	ASTM D5185(m)	>40	0		
	Copper	ppm	ASTM D5185(m)	>330	2		
	Tin	ppm	ASTM D5185(m)	>15	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)		3		
There is no indication of any contamination in the oil	Potassium	ppm	ASTM D5185(m)		<1		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*		0		
	Nitration	Abs/cm	ASTM D7624*	>20	8.6		
	Sulfation	Abs/.1mm	ASTM D7415*	>30	19.9		
	Silt	scalar	Visual*	NONE	VLITE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar		NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	nnm	ASTM D5185(m)		6		
FLOID CONDITION	Boron	ppm	ASTM D5185(m)				
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185(m)		42 0		
	Molybdenum	ppm	ASTM D5185(m)		61		
	Manganese		ASTM D5185(m)		0		
	Magnesium	ppm			1071		
	•	ppm	ASTM D5185(m)				
	Calcium	ppm	ASTM D5185(m)		840 976		
	Phosphorus Zinc	ppm	ASTM D5185(m)		1135		
		ppm	ASTM D5185(m)				
	Sulfur Oxidation	ppm Abo/1mm	ASTM D5185(m)	- OF	2701		
		Abs/.1mm	ASTM D7270(m)	>20	18.3		
	Visc @ 40°C	cSt	ASTM D7279(m)		89.4		
	Visc @ 100°C	cSt	ASTM D2270*		14.4		
	Viscosity Index (VI)	Scale	ASTM D2270*		167		





ISO 17025:2017
Accredited
Laboratory

**Laboratory**: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **Sample No.**: PC0035315 **Received**: 17 May 2024

Test Package: MOB 1 (Additional Tests: KV40, VI, Visual)

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (\*) outside scope of accreditation (m) method modified (a) test

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

CITY OF KIMBERLEY 340 SPOKANE ST KIMBERLEY, BC CA V1A 2E8 Contact: J Hollister

jhollister@kimberley.ca T:

F: