



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
7755
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0120078	GFL0113167	GFL0104507
Sample Date		Client Info		15 May 2024	28 Feb 2024	11 Dec 2023
Machine Age	kms	Client Info		182414	179075	29737
Oil Age	kms	Client Info		30981	0	172203
Filter Age	kms	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>165	13	17	15
Chromium	ppm	ASTM D5185(m)	>5	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>4	0	0	<1
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	0	0	<1
Aluminum	ppm	ASTM D5185(m)	>20	<1	2	2
Lead	ppm	ASTM D5185(m)	>150	0	1	<1
Copper	ppm	ASTM D5185(m)	>90	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>5	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>35	2	3	4
Potassium	ppm	ASTM D5185(m)	>20	1	2	0
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>7.5	1.1	1.5	1.6
Nitration	Abs/cm	ASTM D7624*	>20	9.6	10.4	10.3
Sulfation	Abs/.1mm	ASTM D7415*	>30	22.7	23.3	23.6
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		30	70	39
Boron	ppm	ASTM D5185(m)	0	4	5	2
Barium	ppm	ASTM D5185(m)	0	0	0	<1
Molybdenum	ppm	ASTM D5185(m)	60	63	62	63
Manganese	ppm	ASTM D5185(m)	0	0	0	0
Magnesium	ppm	ASTM D5185(m)	1010	1021	982	990
Calcium	ppm	ASTM D5185(m)	1070	1091	1099	1088
Phosphorus	ppm	ASTM D5185(m)	1150	1042	1042	1003
Zinc	ppm	ASTM D5185(m)	1270	1255	1209	1240
Sulfur	ppm	ASTM D5185(m)	2060	2612	2733	2527
Oxidation	Abs/.1mm	ASTM D7414*	>25	17.0	17.9	17.9
Visc @ 100°C	cSt	ASTM D7279(m)	15.4	14.3	14.2	14.4



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0120078
Lab Number : 02636854
Unique Number : 5786016
Test Package : MOB 1

GFL Environmental - 225 - COT(D2)
 20 Brydon Drive
 Etobicoke, ON
 CA M9W 5R6
 Contact: Rick Philip
 rphilip@gflenv.com
 T: (416)745-8080
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.