



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
CR 23211 Forward Shaft Bearing

Component
Bearing

Fluid
PETRO CANADA BP ENERGOL DS3 153 (20 LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0844561	WC0844564	WC0844536
Sample Date		Client Info		14 May 2024	18 Apr 2024	17 Jan 2024
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Filter Age	mths	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	N/A	Not Changd
Filter Changed		Client Info		None	None	None
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>20	12	12	12
Chromium	ppm	ASTM D5185(m)	>2	0	0	0
Nickel	ppm	ASTM D5185(m)	>2	0	0	<1
Titanium	ppm	ASTM D5185(m)		0	<1	0
Silver	ppm	ASTM D5185(m)		0	0	0
Aluminum	ppm	ASTM D5185(m)	>5	2	1	2
Lead	ppm	ASTM D5185(m)	>25	9	10	9
Copper	ppm	ASTM D5185(m)	>5	<1	<1	<1
Tin	ppm	ASTM D5185(m)	>15	2	2	2
Vanadium	ppm	ASTM D5185(m)		0	0	0
White Metal	scalar	Visual*	NONE	NONE	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>15	12	12	14
Potassium	ppm	ASTM D5185(m)	>20	<1	<1	1
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	Visual*	NONE	NONE	NONE	NONE
Debris	scalar	Visual*	NONE	VLITE	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	NONE
Appearance	scalar	Visual*	NORML	NORML	NORML	NORML
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		4	5	4
Boron	ppm	ASTM D5185(m)		4	2	2
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		<1	<1	1
Manganese	ppm	ASTM D5185(m)		<1	<1	0
Magnesium	ppm	ASTM D5185(m)		34	36	35
Calcium	ppm	ASTM D5185(m)		5070	5087	5218
Phosphorus	ppm	ASTM D5185(m)		827	852	907
Zinc	ppm	ASTM D5185(m)		948	935	966
Sulfur	ppm	ASTM D5185(m)		8836	8691	9596
Visc @ 40°C	cSt	ASTM D7279(m)	99.91	104	105	106



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WC0844561
Lab Number : 02637199
Unique Number : 5786361
Test Package : MAR 1

CANADIAN COAST GUARD
 CCGS CAPE ROGER, PO BOX 5667
 ST. JOHN'S, NL
 CA A1C 5X1
 Contact: Chief Engineer
 caperogerce@ccrg-ngcc.gc.ca
 T: (709)685-6843
 F: (709)685-6059

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.