WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL



Machine Id **LIEBHERR LH50 14799**

Rear Right Wheel Hub

Resample at the next service interval to monitor. Test UOM Method Limit/Abn Current History1 Sample Number Client Info LH0277065 Sample Date Client Info 08 May 2024	History2
Resample at the next service interval to monitor. Sample Number Client Info BMay 2024	
Sample Date Client Info 08 May 2024	
Machine Age hrs Client Info 17000	
Oil Age hrs Client Info 0	
Filter Age hrs Client Info 0	
Oil Changed Client Info Changed	
Filter Changed Client Info N/A	
Sample Status NORMAL	
WEAR Iron ppm ASTM D5185(m) >325 21	
All component wear rates are normal. Chromium ppm ASTM D5185(m) >3 0	
Nickel ppm ASTM D5185(m) >2 0	
Titanium ppm ASTM D5185(m) 0	
Silver ppm ASTM D5185(m) 0	
Aluminum ppm ASTM D5185(m) >10 0	
LeadppmASTM D5185(m)>40	
Copper ppm ASTM D5185(m) >75 1	
Tin ppm ASTM D5185(m) >3 0	
VanadiumppmASTM D5185(m)0	
White Metal scalar Visual* NONE VLITE	
Yellow Metal scalar Visual* NONE NONE	
CONTAMINATION Silicon ppm ASTM D5185(m) >75 2	
There is no indication of any contamination in the oil. Potassium ppm ASTM D5185(m) >20 <1	
Water WC Method >0.2 NEG	
Silt scalar Visual* NONE NONE	
Debris scalar Visual* NONE NONE	
Sand/Dirt scalar Visual* NONE NONE	
Appearance scalar Visual* NORML NORML	
Odor scalar Visual* NORML	
Emulsified Water scalar Visual* >0.2 NEG	
FLUID CONDITION Sodium ppm ASTM D5185(m) 1	
The condition of the oil is acceptable for the time in service. Boron ppm ASTM D5185(m) 15 294	
Barium ppm ASTM D5185(m) 0 0	
MolybdenumppmASTM D5185(m)02	
ManganeseppmASTM D5185(m)0	
MagnesiumppmASTM D5185(m)04	
Calcium ppm ASTM D5185(m) 5 20	
Phosphorus ppm ASTM D5185(m) 600 1525	
Zinc ppm ASTM D5185(m) 0 13	
Sulfur ppm ASTM D5185(m) 22000 18354	
Visc @ 40°C cSt ASTM D7279(m) 140 129 Report Id: BATBBI I IWCAMISI 02637273 (Generated: 05/23/2024 15:31:10) Rev: 1	





CALA ISO 17025:2017 Accredited

Laboratory

Laboratory Sample No.

: LH0277065 Lab Number : 02637273 Unique Number : 5786435

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested**

Diagnosed Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

: 23 May 2024

: 23 May 2024

: 23 May 2024 - Wes Davis

INTERFOR CORP

5060 RTE 430 BRUNSWICK MINE, NB CA E2A 6W6

Contact: Daniel Hachey daniel.hachey@interfor.com T: (506)547-8700

F: (506)548-1892