WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id

092623

Rear Right Final Drive

GEAR OIL SAE 80W90 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm. Please specify the component make and model with your next sample.	Sample Number		Client Info		WC0935792		
	Sample Date		Client Info		15 May 2024		
	Machine Age	hrs	Client Info		492		
	Oil Age	hrs	Client Info		492		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>500	149		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		2		
	Nickel	ppm	ASTM D5185(m)	>10	<1		
	Titanium	ppm	ASTM D5185(m)		<1		
	Silver	ppm	ASTM D5185(m)		<1		
	Aluminum	ppm	ASTM D5185(m)	>25	<1		
	Lead	ppm	ASTM D5185(m)	>25	0		
	Copper	ppm	ASTM D5185(m)	>50	2		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION							
There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185(m)	>75	19		
	Potassium	ppm	ASTM D5185(m)	>20	10		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	Visual*	NONE	VLITE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual* Visual*	NORML >0.2	NORML NEG		
			· · · · · · · · · · · · · · · · · · ·				
FLUID CONDITION	Sodium	ppm	. ,	>170	<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	42		
	Barium	ppm	ASTM D5185(m)	200	10		
	Molybdenum	ppm	ASTM D5185(m)	12	0		
	Manganese	ppm	ASTM D5185(m)	10	3		
	Magnesium	ppm	ASTM D5185(m)		3		
	Calcium	ppm	ASTM D5185(m)	150	19		
	Phosphorus	ppm	ASTM D5185(m)	1650	465		
	Zinc	ppm	ASTM D5185(m)	125	42		
	Sulfur	ppm	ASTM D5185(m)	22500	12986		
enort ld: CGEGLIE IWCAMISI 02637525 (Generated: 05/24/2024 14:23:45) Rev: 1	Visc @ 40°C	cSt	ASTM D7279(m) Contact/Loc:		188		





ISO 17025:2017
Accredited
Laboratory

Laboratory: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **Sample No.**: WC0935792 **Received**: 24 May 2024

 5:2017
 Lab Number
 : 02637525
 Tested
 : 24 May 2024

 Unique Number
 : 5786687
 Diagnosed
 : 24 May 2024 - Wes Davis

Test Package : MOB 1
To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

C.G. EQUIPMENT

7367 Wellington Rd. 30, Unit A Guelph, ON

CA N0M 2T0 Contact: CG Equipment CG Guelph

cory@cgequipment.com T: (519)826-0550

F: (519)837-2055