



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
831003
Component
Natural Gas Engine
Fluid
PETRO CANADA DURON GEO LD 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0112518	GFL0097624	GFL0090602
Sample Date		Client Info		28 May 2024	20 Nov 2023	25 Aug 2023
Machine Age	hrs	Client Info		7697	0	6420
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	Changed
Filter Changed		Client Info		N/A	N/A	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>50	31	21	31
Chromium	ppm	ASTM D5185(m)	>4	1	<1	2
Nickel	ppm	ASTM D5185(m)	>2	<1	<1	1
Titanium	ppm	ASTM D5185(m)		0	0	0
Silver	ppm	ASTM D5185(m)	>3	0	<1	0
Aluminum	ppm	ASTM D5185(m)	>9	3	2	13
Lead	ppm	ASTM D5185(m)	>30	2	1	3
Copper	ppm	ASTM D5185(m)	>35	2	2	2
Tin	ppm	ASTM D5185(m)	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0
White Metal	scalar	Visual*	NONE	NONE	NONE	---
Yellow Metal	scalar	Visual*	NONE	NONE	NONE	---

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>+100	6	18	5
Potassium	ppm	ASTM D5185(m)	>20	4	<1	22
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	ASTM D7844*		0	0	0
Nitration	Abs/cm	ASTM D7624*	>20	12.8	9.7	13.3
Sulfation	Abs/.1mm	ASTM D7415*	>30	26.3	19.4	29.9
Silt	scalar	Visual*	NONE	NONE	NONE	---
Debris	scalar	Visual*	NONE	NONE	NONE	---
Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	---
Appearance	scalar	Visual*	NORML	NORML	NORML	---
Odor	scalar	Visual*	NORML	NORML	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		10	3	10
Boron	ppm	ASTM D5185(m)	50	7	18	11
Barium	ppm	ASTM D5185(m)	5	2	12	0
Molybdenum	ppm	ASTM D5185(m)	50	56	50	63
Manganese	ppm	ASTM D5185(m)	0	1	3	1
Magnesium	ppm	ASTM D5185(m)	560	583	544	687
Calcium	ppm	ASTM D5185(m)	1510	1686	1549	1842
Phosphorus	ppm	ASTM D5185(m)	780	722	726	930
Zinc	ppm	ASTM D5185(m)	870	909	869	1072
Sulfur	ppm	ASTM D5185(m)	2040	1961	1974	2140
Oxidation	Abs/.1mm	ASTM D7414*	>25	21.2	17.1	24.2
Visc @ 100°C	cSt	ASTM D7279(m)	15.1	14.8	14.7	15.5



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0112518 **Received** : 29 May 2024
Lab Number : 02638391 **Tested** : 29 May 2024
Unique Number : 5787553 **Diagnosed** : 29 May 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: Visual)

GFL Environmental - 554 - Edmonton SW
 8409 -15th Street NW
 Edmonton, AB
 CA T6P 0B8
 Contact: Tim Greig
 tgreig@gflenv.com
 T: (780)231-0521
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.