



POWER SYSTEMS
SYSTÈMES DE PUISSANCE

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

[6100299592]

Machine Id

MINTO GENERATOR

Component

Diesel Engine

Fluid

SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WA0021544	---	---
Sample Date		Client Info		28 May 2024	---	---
Machine Age	hrs	Client Info		70	---	---
Oil Age	hrs	Client Info		30	---	---
Filter Age	hrs	Client Info		30	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				NORMAL	---	---

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185(m)	>51	2	---	---
Chromium	ppm	ASTM D5185(m)	>11	0	---	---
Nickel	ppm	ASTM D5185(m)	>5	0	---	---
Titanium	ppm	ASTM D5185(m)		<1	---	---
Silver	ppm	ASTM D5185(m)	>3	0	---	---
Aluminum	ppm	ASTM D5185(m)	>31	<1	---	---
Lead	ppm	ASTM D5185(m)	>26	0	---	---
Copper	ppm	ASTM D5185(m)	>26	<1	---	---
Tin	ppm	ASTM D5185(m)	>4	0	---	---
Vanadium	ppm	ASTM D5185(m)		0	---	---

CONTAMINATION


There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>22	2	---	---
Potassium	ppm	ASTM D5185(m)	>20	0	---	---
Fuel		WC Method	>2.1	<1.0	---	---
Water	%	ASTM D6304*	>0.21	0.044	---	---
ppm Water	ppm	ASTM D6304*	>2100	441	---	---
Glycol	%	ASTM D7922*		0.0	---	---
Soot %	%	ASTM D7844*	>3	0	---	---
Nitration	Abs/cm	ASTM D7624*	>20	4.4	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	18.3	---	---
Emulsified Water	scalar	Visual*	>0.21	.2%	---	---

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>57	<1	---	---
Boron	ppm	ASTM D5185(m)		5	---	---
Barium	ppm	ASTM D5185(m)		0	---	---
Molybdenum	ppm	ASTM D5185(m)		57	---	---
Manganese	ppm	ASTM D5185(m)		0	---	---
Magnesium	ppm	ASTM D5185(m)		947	---	---
Calcium	ppm	ASTM D5185(m)		1029	---	---
Phosphorus	ppm	ASTM D5185(m)		993	---	---
Zinc	ppm	ASTM D5185(m)		1131	---	---
Sulfur	ppm	ASTM D5185(m)		2519	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	12.8	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	14.5	15.1	---	---



ISO 17025:2017
Accredited
Laboratory

Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : WA0021544 **Received** : 30 May 2024
Lab Number : 02638837 **Tested** : 10 Jun 2024
Unique Number : 5787999 **Diagnosed** : 10 Jun 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: Glycol, KF)

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.

Wajax Power Systems
 485 VENTURE DR
 MONCTON, NB
 CA E1H 2P4
 Contact: Doug Balsler
 dbalsler@wajax.com
 T: (506)855-5371
 F: (506)870-4448