**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 


Machine Id


## **CRUISER 3940023140**


Component Starboard Drive

GEAR OIL SAE 75W90 (20 LTR)							
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 75W90. Please confirm.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	OOM	Client Info	Ellille / toll	WC0950380		
	Sample Date		Client Info		28 May 2024		
	Machine Age	kms	Client Info		1500		
	Oil Age	kms	Client Info		10		
	Filter Age	kms	Client Info		10		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>150	4		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)	>25	0		
	Lead	ppm	ASTM D5185(m)	>100	0		
	Copper	ppm	ASTM D5185(m)	>50	<1		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>50	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	<1		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	VLITE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	276		
	Barium	ppm	ASTM D5185(m)	200	0		
	Molybdenum	ppm	ASTM D5185(m)	12	0		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	12	<1		
	Calcium	ppm	ASTM D5185(m)	150	3		
	Phosphorus	ppm	ASTM D5185(m)	1650	1325		
	Zinc	ppm	ASTM D5185(m)	125	6		
	Sulfur	ppm	ASTM D5185(m)	22500	22493		
	Visc @ 40°C	cSt	ASTM D7279(m)	109	104		











CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02638908 Unique Number : 5788070

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : WC0950380 Test Package : MAR 1

**Tested** Diagnosed

: 30 May 2024

: 30 May 2024

: 30 May 2024 - Wes Davis

Contact: CHARLES FARRAN beachesmarine@hotmail.com T: (416)691-0312

**BEACHES MARINE BROKERAGE** 

2146 A QUEEN ST E SUITE 106

F: (866)477-0666

TORONTO, ON

CA M4E 1E3

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.