**WEAR** CONTAMINATION **FLUID CONDITION** 

**NORMAL NORMAL NORMAL** 

Machine Id

TJ036521


Component
Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is SAE 40 Diesel Engine Oil. Please confirm the oil type and grade, and specify the brand of the oil on your next sample. Please specify the component make and model with your next sample.	Sample Number	00111	Client Info		WC0938903		
	Sample Date		Client Info		16 May 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
VEAD							
WEAR	Iron	ppm	ASTM D5185(m)		<1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)		0		
	Nickel	ppm	ASTM D5185(m)	>4	0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		0		
	Aluminum	ppm	ASTM D5185(m)		<1		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)		<1		
	Tin	ppm	ASTM D5185(m)	>15	0		
	Vanadium	ppm	ASTM D5185(m)		0		
ONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	1		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)	>20	0		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*	>3	0		
	Nitration	Abs/cm	ASTM D7624*	>20	5.3		
	Sulfation	Abs/.1mm	ASTM D7415*	>30	17.2		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
LUID CONDITION	Sodium	nnm	ASTM D5185(m)		2		
	Boron	ppm	ASTM D5185(III) ASTM D5185(m)		247		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185(m)		<1		
	Molybdenum	ppm	ASTM D5185(m)		54		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)		357		
	Calcium	ppm	ASTM D5185(m)		1524		
	Phosphorus	ppm	ASTM D5185(m)		950		
	Zinc	ppm	ASTM D5185(m)		1117		
	Sulfur	ppm	ASTM D5185(m)		2685		
	Oxidation	Abs/.1mm	ASTM D7414*	>25	12.9		
	Base Number (BN)	mg KOH/g	ASTM D2896*	0	9.74		
	= accontambor (DIV)				J.1 T		

Visc @ 100°C cSt

ASTM D7279(m)

12.6





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WC0938903 Lab Number : 02639081 Unique Number : 5788243 Test Package : MOB 2

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received **Tested** 

: 03 Jun 2024 Diagnosed

: 03 Jun 2024 - Wes Davis

: 31 May 2024

GENREP LTD. 134 RIVALDA ROAD NORTH YORK, ON CA M9M 2M8 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

T:

F: