

**OIL ANALYSIS REPORT** 

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area


ALKAN AIR LTD. [53330]

C208B 123238 (S/N 0904)

Jet Turbine

BP TURBO OIL 2380 (--- GAL)

RECOMMENDATION					/		
HEOOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		GT57835	GT57064	GT57061
	Sample Date		Client Info		26 May 2024	01 May 2024	12 Nov 2023
	Machine Age	hrs	Client Info		0	0	0
	Oil Age	hrs	Client Info		880	770	683
	Filter Age	hrs	Client Info		100	99	84
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL		NORMAL
WEAR	Iron	ppm	ASTM D5185(m)	>8	<1	<1	<1
	Chromium	ppm	ASTM D5185(m)	>2	0	0	0
	Nickel	ppm	ASTM D5185(m)	>2	0	0	0
	Silver	ppm	ASTM D5185(m)	>2	0	0	0
	Aluminum	ppm	ASTM D5185(m)	>2	<1	<1	1
	Lead	ppm	ASTM D5185(m)	>3	<1	<1	<1
	Copper	ppm	ASTM D5185(m)	>3	0	0	0
CONTAMINATION	Water		WC Method	>0.1	NEG	NEG	NEG
FLUID CONDITION	Magnesium	ppm	ASTM D5185(m)	0	0	0	0
	Acid Number (AN)	mg KOH/g	ASTM D974*	0.43	0.93	0.83	0.98
	Visc @ 40°C	cSt	ASTM D7279(m)	24.2	24.7		24.5





CALA ISO 17025:2017 Accredited

Laboratory

Laboratory Sample No.

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : GT57835 Lab Number : 02639534

Unique Number : 5788696

Received Tested

Diagnosed

: 03 Jun 2024 : 03 Jun 2024

Oct3/23

: 03 Jun 2024 - Wes Davis

**Honeywell Engines** 111 S. 34th Street, 301 Receiving, Attn: SOAP Program PHOENIX, AZ

US 85034 Contact: GARRETT

Test Package : G331 ( Additional Tests: ICP ) To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.

T: F: (602)365-2676