**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 



## Machine Id LIEBHERR LH50M 1216-98210

Front Left Wheel Hub

GEAR OIL SAE 80W90 ( GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LH0290691	LHMC103328	
	Sample Date		Client Info		27 May 2024	19 Oct 2018	
	Machine Age	hrs	Client Info		1000	1875	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		None	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185(m)	>325	70	58	
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>3	<1	<1	
	Nickel	ppm	ASTM D5185(m)	>2	<1	<1	
	Titanium	ppm	ASTM D5185(m)	>4	0	0	
	Silver	ppm	ASTM D5185(m)	>2	0	0	
	Aluminum	ppm	ASTM D5185(m)	>10	<1	<1	
	Lead	ppm	ASTM D5185(m)	>3	0	0	
	Copper	ppm	ASTM D5185(m)	>70	11	12	
	Tin	ppm	ASTM D5185(m)	>2	0	0	
	Vanadium	ppm	ASTM D5185(m)		0	0	
	White Metal	scalar	Visual*	NONE	NONE	MODER	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>70	3	0	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185(m)		1	0	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	Visual*	NONE	VLITE	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>170	7	6	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	28	2	
	Barium	ppm	ASTM D5185(m)	200	0	0	
	Molybdenum	ppm	ASTM D5185(m)	12	0	13	
	Manganese	ppm	ASTM D5185(m)		1	1	
	Magnesium	ppm	ASTM D5185(m)	12	6	5	
	Calcium	ppm	ASTM D5185(m)	150	39	98	
	Phosphorus	ppm	ASTM D5185(m)	1650	1202	1089	
	Zinc	ppm	ASTM D5185(m)	125	16	38	
	Sulfur	ppm	ASTM D5185(m)	22500	15377	16615	
	Visc @ 40°C	cSt	ASTM D7279(m)	143	128	152.2	





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: LH0290691 Lab Number : 02639685 Unique Number : 5788847 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 04 Jun 2024 **Tested** : 05 Jun 2024

Diagnosed : 05 Jun 2024 - Wes Davis

Contact: BOB LANCE T:

SIMS BROTHERS

MARION, OH

US 43302

F:

1011 S. PROSPECT ST

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.