
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**



Machine Id **LIEBHERR LH50M 1216-98210**

Front Right Wheel Hub

GEAR OIL SAE 80W90 (GAL))						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LH0290693	LHMC103354	
	Sample Date		Client Info		27 May 2024	19 Oct 2018	
	Machine Age	hrs	Client Info		1000	1875	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		None	N/A	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185(m)	>325	42	51	
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>3	0	<1	
	Nickel	ppm	ASTM D5185(m)		0	<1	
	Titanium	ppm	ASTM D5185(m)	>4	0	0	
	Silver	ppm	ASTM D5185(m)	>2	0	0	
	Aluminum	ppm	ASTM D5185(m)	>10	<1	1	
	Lead	ppm	ASTM D5185(m)	>3	0	0	
	Copper	ppm	ASTM D5185(m)	>70	6	12	
	Tin	ppm	ASTM D5185(m)	>2	0	0	
	Vanadium	ppm	ASTM D5185(m)		0	0	
	White Metal	scalar	Visual*	NONE	NONE	MODER	
	Yellow Metal	scalar	Visual*	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>70	<1	1	
	Potassium	ppm	ASTM D5185(m)	>20	1	<1	
There is no indication of any contamination in the oil.	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	Visual*	NONE	LIGHT	NONE	
	Debris	scalar	Visual*	NONE	NONE	NONE	
	Sand/Dirt	scalar	Visual*	NONE	NONE	NONE	
	Appearance	scalar	Visual*	NORML	NORML	NORML	
	Odor	scalar	Visual*	NORML	NORML	NORML	
	Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>170	6	6	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	400	33	2	
The contained are on a acceptable for the time in convice.	Barium	ppm	ASTM D5185(m)	200	0	0	
	Molybdenum	ppm	ASTM D5185(m)	12	0	12	
	Manganese	ppm	ASTM D5185(m)		<1	1	
	Magnesium	ppm	ASTM D5185(m)	12	3	5	
	Calcium	ppm	ASTM D5185(m)	150	31	106	
	Phosphorus	ppm	ASTM D5185(m)	1650	1207	1142	
	Zinc	ppm	ASTM D5185(m)	125	12	40	
	Sulfur	ppm	ASTM D5185(m)		15321	16856	
Papart Id. CIMMADI LI IN/CAMICI 02020000 (Caparated: 06/05/2024 12:45:20) Pays 1	Visc @ 40°C	cSt	ASTM D7279(m)	143	128	152.3	







Laboratory Sample No.

Lab Number : 02639688 Unique Number : 5788850

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : LH0290693 Test Package : MOB 1

Received **Tested**

: 05 Jun 2024 Diagnosed

: 05 Jun 2024 - Wes Davis

: 04 Jun 2024

US 43302 Contact: BOB LANCE

> T: F:

SIMS BROTHERS

MARION, OH

1011 S. PROSPECT ST

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.