



WEAR	<b>ABNORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**1254**  
Component  
**Transmission (Manual)**  
Fluid  
**TES SYN 295 (--- GAL)**

**RECOMMENDATION**

We recommend that you drain the fluid from the component if this has not already been done. We recommend an early resample to monitor this condition. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) TES SYN 295. Please confirm. Please specify the component make and model with your next sample.

**WEAR**

Aluminum ppm levels are abnormal. Torque converter wear is indicated.












**CONTAMINATION**

There is no indication of any contamination in the fluid.

**FLUID CONDITION**

The fluid is no longer serviceable as a result of the abnormal and/or severe wear.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PC0085121</b>	PC0083532	PC0083680
Sample Date		Client Info		<b>11 Jun 2024</b>	07 Jan 2024	26 Dec 2023
Machine Age	kms	Client Info		<b>97648</b>	4464	4452
Oil Age	kms	Client Info		<b>0</b>	0	0
Filter Age	kms	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	N/A	N/A
Filter Changed		Client Info		<b>N/A</b>	N/A	N/A
Sample Status				<b>ABNORMAL</b>	ABNORMAL	ABNORMAL
Iron	ppm	ASTM D5185(m)	>200	<b>125</b>	118	117
Chromium	ppm	ASTM D5185(m)	>5	<b>0</b>	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	<1	1
Titanium	ppm	ASTM D5185(m)		<b>0</b>	0	0
Silver	ppm	ASTM D5185(m)	>7	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185(m)	>25	<b>▲ 34</b>	<b>▲ 27</b>	<b>▲ 28</b>
Lead	ppm	ASTM D5185(m)	>45	<b>42</b>	40	42
Copper	ppm	ASTM D5185(m)	>225	<b>15</b>	13	13
Tin	ppm	ASTM D5185(m)	>10	<b>5</b>	4	4
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	0	0
White Metal	scalar	Visual*	NONE	<b>VLITE</b>	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Silicon	ppm	ASTM D5185(m)	>125	<b>7</b>	4	6
Potassium	ppm	ASTM D5185(m)	>20	<b>5</b>	5	6
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	Visual*	NONE	<b>NONE</b>	VLITE	NONE
Debris	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	Visual*	NONE	<b>VLITE</b>	NONE	LIGHT
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	<b>NEG</b>	NEG	NEG
Sodium	ppm	ASTM D5185(m)		<b>6</b>	6	6
Boron	ppm	ASTM D5185(m)	85	<b>105</b>	101	98
Barium	ppm	ASTM D5185(m)	0	<b>1</b>	<1	<1
Molybdenum	ppm	ASTM D5185(m)	0	<b>&lt;1</b>	1	1
Manganese	ppm	ASTM D5185(m)	0	<b>2</b>	2	2
Magnesium	ppm	ASTM D5185(m)	1	<b>1</b>	<1	1
Calcium	ppm	ASTM D5185(m)	100	<b>43</b>	38	41
Phosphorus	ppm	ASTM D5185(m)	200	<b>268</b>	265	262
Zinc	ppm	ASTM D5185(m)	0	<b>6</b>	5	5
Sulfur	ppm	ASTM D5185(m)	1500	<b>628</b>	673	651
Visc @ 40°C	cSt	ASTM D7279(m)	37.0	<b>36.0</b>	36.3	36.3
Visc @ 100°C	cSt	ASTM D7279(m)	7.3	<b>7.1</b>	7.1	7.1
Viscosity Index (VI)	Scale	ASTM D2270*	165	<b>164</b>	162	162



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : PC0085121  
**Lab Number** : 02641464  
**Unique Number** : 5799003  
**Test Package** : MOB 1 ( Additional Tests: KV100, VI )

**LES ENTREPRISES MICHAUDVILLE INC.**  
 270 RUE BRUNET  
 MONT ST-HILAIRE, QC  
 CA J3H 0M6  
 Contact: Martin Trudel  
 mtrudel@michaudville.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.