



# LIEBHERR

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**059596-194**

Component  
**Splitter Box**

Fluid  
**PETRO CANADA TRAXON 75W90 SYNTHETIC (3 LTR)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LH0289614</b>	LH0285116	LH0274782
Sample Date		Client Info		<b>09 Jun 2024</b>	07 Feb 2024	23 Nov 2023
Machine Age	hrs	Client Info		<b>19988</b>	19498	19244
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>None</b>	None	None
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>275	<b>34</b>	39	2
Chromium	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185(m)	>5	<b>0</b>	0	0
Titanium	ppm	ASTM D5185(m)		<b>&lt;1</b>	<1	0
Silver	ppm	ASTM D5185(m)	>2	<b>0</b>	0	<1
Aluminum	ppm	ASTM D5185(m)	>10	<b>&lt;1</b>	<1	<1
Lead	ppm	ASTM D5185(m)	>5	<b>0</b>	0	<1
Copper	ppm	ASTM D5185(m)	>40	<b>&lt;1</b>	<1	15
Tin	ppm	ASTM D5185(m)	>4	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	0	0
White Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION










There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>30	<b>2</b>	3	3
Potassium	ppm	ASTM D5185(m)	>20	<b>0</b>	<1	0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	Visual*	NONE	<b>NONE</b>	NONE	VLITE
Debris	scalar	Visual*	NONE	<b>NONE</b>	NONE	VLITE
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	Visual*	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	Visual*	>0.1	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)	>25	<b>&lt;1</b>	<1	<1
Boron	ppm	ASTM D5185(m)	328	<b>295</b>	286	297
Barium	ppm	ASTM D5185(m)	1	<b>0</b>	0	<1
Molybdenum	ppm	ASTM D5185(m)		<b>0</b>	<1	0
Manganese	ppm	ASTM D5185(m)		<b>&lt;1</b>	0	0
Magnesium	ppm	ASTM D5185(m)	1	<b>6</b>	10	<1
Calcium	ppm	ASTM D5185(m)	7	<b>24</b>	25	6
Phosphorus	ppm	ASTM D5185(m)	1145	<b>1183</b>	1257	1222
Zinc	ppm	ASTM D5185(m)	3	<b>62</b>	36	16
Sulfur	ppm	ASTM D5185(m)	17909	<b>18938</b>	20192	20593
Visc @ 40°C	cSt	ASTM D7279(m)	99.6	<b>87.0</b>	94.4	106



ISO 17025:2017  
Accredited  
Laboratory

**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9

**Sample No.** : LH0289614

**Lab Number** : 02641492

**Unique Number** : 5799031

**Test Package** : MOB 1

**Received** : 12 Jun 2024

**Tested** : 12 Jun 2024

**Diagnosed** : 12 Jun 2024 - Wes Davis

**American Iron and Metal**

2555 Sheffield Road

Ottawa, ON

CA K1B 3V6

Contact: Dan Dupelle

ddupelle@aim-rg.com

T: (613)228-9380

F: (613)745-0692

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.