

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



LIEBHERR L550 076577-1825

Front Differential

GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.

WEAR

Metal levels are typical for a new component breaking in.

CONTAMINATION


There is no indication of any contamination in the oil.


FLUID CONDITION

The condition of the oil is acceptable for the time in service.

				.,		
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LH0290657		
Sample Date		Client Info		11 Jun 2024		
Machine Age	hrs	Client Info		541		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
			4050			
Iron	ppm	ASTM D5185(m)	>1250	212		
Chromium	ppm	ASTM D5185(m)	>6	2		
Nickel	ppm	ASTM D5185(m)	>4	4		
Titanium	ppm	ASTM D5185(m)		0		
Silver	ppm	ASTM D5185(m)	05	0		
Aluminum	ppm	ASTM D5185(m)	>35	2		
Lead	ppm	ASTM D5185(m)	>4	1		
Copper	ppm	ASTM D5185(m)	>30	63		
Tin	ppm	ASTM D5185(m)	>4	5		
Vanadium	ppm	ASTM D5185(m)	NONE	0		
White Metal	scalar	Visual*	NONE	VLITE		
Yellow Metal	scalar	Visual*	NONE	NONE		
Silicon	ppm	ASTM D5185(m)	>100	25		
Potassium	ppm	ASTM D5185(m)	>20	<1		
Water		WC Method	>.2	NEG		
Silt	scalar	Visual*	NONE	LIGHT		
Debris	scalar	Visual*	NONE	NONE		
Sand/Dirt	scalar	Visual*	NONE	NONE		
Appearance	scalar	Visual*	NORML	NORML		
Odor	scalar	Visual*	NORML	NORML		
Emulsified Water	scalar	Visual*	>.2	NEG		
Sodium	ppm	ASTM D5185(m)	>170	5		
Boron	ppm	ASTM D5185(m)	400	3		
Barium	ppm	ASTM D5185(m)	200	ء <1		
Molybdenum	ppm	ASTM D5185(m)	12	0		
Manganese	ppm	ASTM D5185(m)	•	16		
Magnesium	ppm	ASTM D5185(m)	12	5		
Calcium	ppm	ASTM D5185(m)	150	8		
Phosphorus	ppm	ASTM D5185(m)	1650	2206		
Zinc	ppm	ASTM D5185(m)	125	21		
Sulfur	ppm	ASTM D5185(m)	22500	24993		
Visc @ 40°C	cSt	ASTM D7279(m)	143	193		

Submitted By: Eric Leblond





Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 142975 CANADA LTEE (MIRONOR) CALA 回偷 . Sample No. Received : 14 Jun 2024 751 CH DE LA 2E CONCESSION : LH0290657 Lab Number : 02642080 Tested BROWNSBURG-CHATHAM, QC : 14 Jun 2024 ISO 17025:2017 Accredited Laboratory Diagnosed Unique Number : 5799619 : 17 Jun 2024 - Kevin Marson CA J8G 1S9 Test Package : MOB 1 Contact: Francis Sylvestre To discuss this sample report, contact Customer Service at 1-800-268-2131. T: (450)898-9225 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied. F:

Submitted By: Eric Leblond

Page 2 of 2