



Machine Id  
**930016**  
Component  
**Transmission (Auto)**  
Fluid  
**PETRO CANADA DuraDrive HD Synthetic 668 (--- GAL)**

### RECOMMENDATION

Nous vous recommandons de vidanger le fluide de ce composant si vous ne l'avez pas déjà fait. Confirmez la source du lubrifiant utilisé pour l'appoint/remplissage. Nous vous recommandons d'échantillonner de nouveau dès que possible afin de contrôler la situation.

### WEAR

Usure de disque d'embrayage.













### CONTAMINATION

Il n'y a aucun indice de contamination dans le fluide.

### FLUID CONDITION

Les niveaux d'additifs indiquent l'ajout d'une autre marque ou d'un autre type d'huile. Le fluide n'est plus en état de service en raison d'une usure anormale et/ou sévère.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PC0088608</b>	---	---
Sample Date		Client Info		<b>03 Jun 2024</b>	---	---
Machine Age	kms	Client Info		<b>126276</b>	---	---
Oil Age	kms	Client Info		<b>0</b>	---	---
Filter Age	kms	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>N/A</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>ABNORMAL</b>	---	---
Iron	ppm	ASTM D5185(m)	>220	<b>139</b>	---	---
Chromium	ppm	ASTM D5185(m)	>2	<b>&lt;1</b>	---	---
Nickel	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	---	---
Titanium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Silver	ppm	ASTM D5185(m)	>5	<b>0</b>	---	---
Aluminum	ppm	ASTM D5185(m)	>75	<b>60</b>	---	---
Lead	ppm	ASTM D5185(m)	>95	<b>▲ 96</b>	---	---
Copper	ppm	ASTM D5185(m)	>60	<b>42</b>	---	---
Tin	ppm	ASTM D5185(m)	>10	<b>8</b>	---	---
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	---	---
White Metal	scalar	Visual*	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	Visual*	NONE	<b>NONE</b>	---	---
Silicon	ppm	ASTM D5185(m)	>25	<b>9</b>	---	---
Potassium	ppm	ASTM D5185(m)	>20	<b>6</b>	---	---
Water		WC Method	>0.1	<b>NEG</b>	---	---
Silt	scalar	Visual*	NONE	<b>NONE</b>	---	---
Debris	scalar	Visual*	NONE	<b>VLITE</b>	---	---
Sand/Dirt	scalar	Visual*	NONE	<b>NONE</b>	---	---
Appearance	scalar	Visual*	NORML	<b>NORML</b>	---	---
Odor	scalar	Visual*	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	Visual*	>0.1	<b>NEG</b>	---	---
Sodium	ppm	ASTM D5185(m)		<b>10</b>	---	---
Boron	ppm	ASTM D5185(m)	78	<b>73</b>	---	---
Barium	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Molybdenum	ppm	ASTM D5185(m)	0	<b>&lt;1</b>	---	---
Manganese	ppm	ASTM D5185(m)		<b>2</b>	---	---
Magnesium	ppm	ASTM D5185(m)	0	<b>&lt;1</b>	---	---
Calcium	ppm	ASTM D5185(m)	113	<b>● 42</b>	---	---
Phosphorus	ppm	ASTM D5185(m)	222	<b>261</b>	---	---
Zinc	ppm	ASTM D5185(m)		<b>● 31</b>	---	---
Sulfur	ppm	ASTM D5185(m)	1326	<b>● 668</b>	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	34.8	<b>35.2</b>	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	7.0	<b>7.0</b>	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	167	<b>164</b>	---	---



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : PC0088608  
**Lab Number** : 02642615  
**Unique Number** : 5800154  
**Test Package** : MOB 1 ( Additional Tests: KV100, VI )

**GFL Environmental - 742 - Quebec City Solid Waste**  
 5160 Jean-Talon Pierre-Bertrand Bou  
 Quebec City, QC  
 CA G2J 1B7  
 Contact: Jean Audet  
 Jaudet@matrec.ca  
 T: (418)624-0080  
 F:

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.