WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Machine Id SV026

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DIESEL ENGINE OIL SAE 15W40. Please confirm. Please specify the component make and model with your next sample.	Sample Number		Client Info		WC0938900		
	Sample Date		Client Info		18 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)		2		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>20	0		
	Nickel	ppm	ASTM D5185(m)	>4	0		
	Titanium	ppm	ASTM D5185(m)		<1		
	Silver	ppm	ASTM D5185(m)	>3	<1		
	Aluminum	ppm	ASTM D5185(m)	>20	1		
	Lead	ppm	ASTM D5185(m)	>40	0		
	Copper	ppm	ASTM D5185(m)	>330	13		
	Tin	ppm	ASTM D5185(m)	>15	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	7		
	Potassium	ppm	ASTM D5185(m)	>20	<1		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*	>3	0		
	Nitration	Abs/cm	ASTM D7624*	>20	4.4		
	Sulfation	Abs/.1mm	ASTM D7415*	>30	18.9		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	VLITE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water			>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>158	<1		
	Boron	ppm	ASTM D5185(m)	250	343		
The BN result indicates that there is suitable alkalinity remaining in the	Barium	ppm	ASTM D5185(m)	10	0		
oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Molybdenum	ppm	ASTM D5185(m)	100	77		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	450	369		
	Calcium	ppm	ASTM D5185(m)	3000	1375		
	Phosphorus	ppm	ASTM D5185(m)	1150	978		
	Zinc	ppm	ASTM D5185(m)	1350	1099		
	Sulfur	ppm	ASTM D5185(m)	4250	2655		
	Oxidation	Abs/.1mm	ASTM D7414*	>25	13.2		
	Acid Number (AN)	mg KOH/g	ASTM D974*		2.39		
	Base Number (BN)	mg KOH/g	ASTM D2896*	8.5	8.11		
	Visc @ 40°C	cSt	ASTM D7279(m)	115	94.6		
	Visc @ 100°C	cSt	ASTM D7279(m)	14.4	13.3		
	Viscosity Index (VI)				140		
	, ()						





CALA
Terry
Acceptation 1: 100:011

ISO 17025:2017
Accredited

Laboratory: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **Sample No.**: WC0938900 **Received**: 19 Jun 2024

Lab Number : 02642750 Tested : 20 Jun 2024

Unique Number : 5800289 Diagnosed : 20 Jun 2024 - Kevin Marson

Test Package : MOB 2 (Additional Tests: KV40, TAN Auto, TAN Man, VI, Visual)

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Contact: Service Manager

T:

F: