WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**


Machine Id

TJ037449

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DIESEL ENGINE OIL SAE 15W40. Please confirm. Please specify the component make and model with your next sample.	Sample Number		Client Info		WC0954230		
	Sample Date		Client Info		11 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	\100	2		
WEAIT	Chromium	ppm	ASTM D5185(m)		0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)	>3	<1		
	Aluminum	ppm	ASTM D5185(m)		1		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)		2		
	Tin	ppm	ASTM D5185(m)		0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	VLITE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	4		
	Potassium	ppm	ASTM D5185(m)	>20	3		
There is no indication of any contamination in the oil.	Fuel			>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	ASTM D7844*		0		
	Nitration	Abs/cm	ASTM D7624*	>20	4.2		
	Sulfation	Abs/.1mm		>30	19.7		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	visuai"	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	>158	3		
The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185(m)		262		
	Barium	ppm	ASTM D5185(m)	10	0		
	Molybdenum	ppm	ASTM D5185(m)	100	74		
	Manganese	ppm	ASTM D5185(m)		0		
	Magnesium	ppm	ASTM D5185(m)	450	560		
	Calcium	ppm	ASTM D5185(m)	3000	1210		
	Phosphorus	ppm	ASTM D5185(m)	1150	974		
	Zinc	ppm	ASTM D5185(m)	1350	1109		
	Sulfur	ppm	ASTM D5185(m)	4250	2636		
	Oxidation	Abs/.1mm	ASTM D7414*	>25	15.0		
	Acid Number (AN)	mg KOH/g			2.15		
	Base Number (BN)	mg KOH/g		8.5	8.71		
	Visc @ 40°C	cSt	ASTM D7279(m)		109		
	Visc @ 100°C	cSt	ASTM D7279(m)		14.4		
	Viscosity Index (VI)	Scale	ASTM D2270*	126	134		





ISO 17025:2017
Accredited
Laboratory

Laboratory: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **Sample No.**: WC0954230 **Received**: 19 Jun 2024

Lab Number : 02642752 Tested : 20 Jun 2024

Unique Number : 5800291 Diagnosed : 20 Jun 2024 - Kevin Marson

Test Package: MOB 2 (Additional Tests: KV40, TAN Auto, TAN Man, VI, Visual) To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

Contact: Service Manager

T:

F: