



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1152
 Component
Diesel Engine
 Fluid
PETRO CANADA 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0125049	GFL0090736	GFL0069697
Sample Date		Client Info		12 Jun 2024	15 Aug 2023	24 Jan 2023
Machine Age	hrs	Client Info		19168	17801	16457
Oil Age	hrs	Client Info		600	600	600
Filter Age	hrs	Client Info		600	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>165	22	46	27
Chromium	ppm	ASTM D5185(m)	>5	<1	2	<1
Nickel	ppm	ASTM D5185(m)	>4	<1	0	<1
Titanium	ppm	ASTM D5185(m)	>2	0	0	<1
Silver	ppm	ASTM D5185(m)	>2	0	0	0
Aluminum	ppm	ASTM D5185(m)	>20	3	3	3
Lead	ppm	ASTM D5185(m)	>150	1	14	7
Copper	ppm	ASTM D5185(m)	>90	<1	2	2
Tin	ppm	ASTM D5185(m)	>5	0	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>35	4	5	5
Potassium	ppm	ASTM D5185(m)	>20	4	4	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	ASTM D7844*	>7.5	0.3	0.6	0.4
Nitration	Abs/cm	ASTM D7624*	>20	10.5	15.0	12.4
Sulfation	Abs/.1mm	ASTM D7415*	>30	22.5	30.5	26.6
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		1	3	3
Boron	ppm	ASTM D5185(m)		1	4	20
Barium	ppm	ASTM D5185(m)		0	0	0
Molybdenum	ppm	ASTM D5185(m)		65	78	72
Manganese	ppm	ASTM D5185(m)		<1	<1	<1
Magnesium	ppm	ASTM D5185(m)		1023	1268	950
Calcium	ppm	ASTM D5185(m)		1107	1422	1574
Phosphorus	ppm	ASTM D5185(m)		1081	1342	1263
Zinc	ppm	ASTM D5185(m)		1269	1562	1440
Sulfur	ppm	ASTM D5185(m)		2553	2774	2809
Oxidation	Abs/.1mm	ASTM D7414*	>25	19.6	▲ 28.0	23.5
Visc @ 100°C	cSt	ASTM D7279(m)		11.7	13.0	12.1



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : GFL0125049
Lab Number : 02642812
Unique Number : 5800351
Test Package : MOB 1

GFL Environmental - 504 - Edmonton
 12015 28 Street NE
 Edmonton, AB
 CA T6S 1E2
 Contact: Jerrod Adair
 jerrodadair@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.