

OIL ANALYSIS REPORT

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Area


(N/A) LATITUDE AIR AMBULANCE [53395] [N/A] LEARJET LJ35 NO UNIT GT55336 (S/N 394)


Right Jet Turbine


MOBIL JET OIL 254 (--- GAL)

RECOMMENDATION	- .			1.5 - 5 / 61			
	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		GT55336		
	Sample Date		Client Info		14 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		450		
	Filter Age	hrs	Client Info		235		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR			AOTH DE (OF)				
WEAR	Iron	ppm	ASTM D5185(m)		1		
	Chromium	ppm	ASTM D5185(m)	>2	0		
	Nickel	ppm	ASTM D5185(m)	>2	0		
	Silver	ppm	ASTM D5185(m)	>2	<1		
	Aluminum	ppm	ASTM D5185(m)	>2	1		
	Lead	ppm	ASTM D5185(m)	>3	1		
	Copper	ppm	ASTM D5185(m)	>3	0		
CONTAMINATION	Water		WC Method	>0.1	NEG		
FLUID CONDITION	Magnesium	ppm	ASTM D5185(m)	0	0		
	Visc @ 40°C	cSt	ASTM D7279(m)	26.4	27.6		











CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02643061

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 : GT55336

Unique Number : 5800600 Test Package : G731 (Additional Tests: ICP)

Received **Tested** Diagnosed

: 19 Jun 2024 : 19 Jun 2024

: 19 Jun 2024 - Wes Davis

Honeywell Engines 111 S. 34th Street, 301 Receiving, Attn: SOAP Program PHOENIX, AZ

Contact/Location: GARRETT ? - HONPHO

US 85034 Contact: GARRETT

To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

F: (602)365-2676