
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

[157457]
Machine Id
5KH866
Component
Transmission
Fluid

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number	UOIVI	Client Info	LIIIII/AUII	CU0021217		
Resample at the next service interval to monitor.	Sample Date		Client Info		18 Jun 2024		
	Machine Age	hrs	Client Info		2092		
	Oil Age		Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	1113	Client Info		Not Changd		
	Filter Changed		Client Info		Not Change		
	Sample Status		Olletti IIIIO		NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>200	13		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>10	0		
	Nickel	ppm	ASTM D5185(m)		<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		3		
	Aluminum	ppm	ASTM D5185(m)	>50	<1		
	Lead	ppm	ASTM D5185(m)	>50	10		
	Copper	ppm	ASTM D5185(m)	>200	117		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Ciliana		ACTM DE10F()		•		
CONTAINMATION	Silicon	ppm	ASTM D5185(m)		2		
There is no indication of any contamination in the fluid.	Potassium Water	ppm	ASTM D5185(m) WC Method	>0.1	<1 NEC		
		cooler	Visual*		NEG		
	Silt Debris	scalar scalar	Visual*	NONE	NONE NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
			Visual*	NORML	NORML		
	Appearance Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water		Visual*	>0.1	NEG		
			· · · · · · · · · · · · · · · · · · ·				
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		2		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)		10		
	Barium	ppm	ASTM D5185(m)		0		
	Molybdenum	ppm	ASTM D5185(m)		62		
	Manganese	ppm	ASTM D5185(m)		<1		
	Magnesium	ppm	ASTM D5185(m)		143		
	Calcium	ppm	ASTM D5185(m)		2271		
	Phosphorus	ppm	ASTM D5185(m)		767		
	Zinc	ppm	ASTM D5185(m)		859		
	Sulfur	ppm	ASTM D5185(m)		5897		
	Visc @ 40°C	cSt	ASTM D7279(m)	95.0	105		





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

Lab Number : 02643435 Unique Number : 5800974

: CU0021217 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 21 Jun 2024 **Tested** : 21 Jun 2024 Diagnosed

: 21 Jun 2024 - Wes Davis

CUMMINS EASTERN CANADA LP

6950 EDWARDS BLVD MISSISSAUGA, ON CA L5T 2W2

Contact: Jeffrey Moore jeffrey.moore@cummins.com T: (905)795-0050

F: (905)795-0035