WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL **NORMAL**

Machine Id

091764
Component
Transmission (Manual)

TDTO FLUID SAE 10W (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) TDTO FLUID SAE 10W. Please confirm.	Sample Number		Client Info		WC0692625		
	Sample Date		Client Info		28 May 2024		
	Machine Age	hrs	Client Info		4638		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185(m)	>200	19		
All component wear rates are normal.	Chromium	ppm	ASTM D5185(m)	>5	0		
	Nickel	ppm	ASTM D5185(m)	>5	<1		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)	>7	<1		
	Aluminum	ppm	ASTM D5185(m)	>25	<1		
	Lead	ppm	ASTM D5185(m)	>45	0		
	Copper	ppm	ASTM D5185(m)	>225	8		
	Tin	ppm	ASTM D5185(m)	>10	0		
	Vanadium	ppm	ASTM D5185(m)		0		
	White Metal	scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>125	4		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185(m)	>20	3		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	NONE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)		2		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185(m)	37	48		
	Barium	ppm	ASTM D5185(m)	7	<1		
	Molybdenum	ppm	ASTM D5185(m)	5	<1		
	Manganese	ppm	ASTM D5185(m)		<1		
	Magnesium	ppm	ASTM D5185(m)	40	22		
	Calcium	ppm	ASTM D5185(m)	2650	2505		
	Phosphorus	ppm	ASTM D5185(m)	1050	945		
	Zinc	ppm	ASTM D5185(m)	1075	1045		
	Sulfur	ppm	ASTM D5185(m)	5750	2544		
	Visc @ 40°C	cSt	ASTM D7279(m)	40	50.3		
Report Id: CGEZUR [WCAMIS] 02643785 (Generated: 06/24/2024 16:31:53) Rev: 1			(Contact/l	Location: Dw	ayne Martin	- CGEZUR





CALA ISO 17025:2017 Accredited Laboratory

Laboratory Sample No.

: WC0692625 Lab Number : 02643785 Unique Number : 5801324 Test Package : MOB 1

: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 Received : 24 Jun 2024 **Tested** : 24 Jun 2024 Diagnosed

: 24 Jun 2024 - Wes Davis

Contact: Dwayne Martin dwayne@cgequipment.com

T: (519)236-4099 F: (519)236-7330

C G EQUIPMENT

38 MAIN STREET

ZURICH, ON

CA NOM 2TO

To discuss this sample report, contact Customer Service at 1-800-268-2131. Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

Validity of results and interpretation are based on the sample and information as supplied.