WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

[87053]

48 TORONTO RD FLESHERTON BELL CANADA 9536383

Left Diesel Engine

ESSO XD-3 EXTRA 15W40 (--- LTR)

ESSO XD-3 EXTRA 15W40 (LTR)					-,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
1120011111211211	Sample Number		Client Info		PN0006313		
Resample at the next service interval to monitor.	Sample Date		Client Info		19 Jun 2024		
	Machine Age	hrs	Client Info		53		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed	0	Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status		Oliciti iiilo		NORMAL		
<u></u>					····		
WEAR	Iron	ppm	ASTM D5185(m)	>150	7		
	Chromium	ppm	ASTM D5185(m)	>20	1		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185(m)		0		
	Titanium	ppm	ASTM D5185(m)		0		
	Silver	ppm	ASTM D5185(m)		<1		
	Aluminum	ppm	ASTM D5185(m)		2		
	Lead	ppm	ASTM D5185(m)		0		
	Copper	ppm	ASTM D5185(m)		7		
	Tin	ppm	ASTM D5185(m)		/ <1		
	Vanadium	ppm	ASTM D5185(m)	>10	0		
	White Metal		. ,	NONE	NONE		
		scalar	Visual*	NONE	NONE		
	Yellow Metal	scalar	Visual*	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185(m)	>25	15		
CONTAININATION	Potassium	ppm	ASTM D5185(m)		2		
There is no indication of any contamination in the oil.	Fuel	ррпп	WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method	<i>></i> 0.2	NEG		
	Soot %	%	ASTM D7844*	~ 3	0		
			ASTM D7644*				
	Nitration	Abs/tmm		>20	7.5		
	Sulfation Silt	Abs/.1mm	ASTM D7415*		19.5		
		scalar	Visual*	NONE	NONE		
	Debris	scalar	Visual*	NONE	VLITE		
	Sand/Dirt	scalar	Visual*	NONE	NONE		
	Appearance	scalar	Visual*	NORML	NORML		
	Odor	scalar	Visual*	NORML	NORML		
	Emulsified Water	scalar	Visual*	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185(m)	\192	8		
TEOID CONDITION	Boron	ppm	ASTM D5185(m)	/ IUL	64		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185(m)		<1		
	Molybdenum	ppm	ASTM D5185(m)		42		
	Manganese	ppm	ASTM D5185(m)		2		
	-		ASTM D5185(m)				
	Magnesium	ppm		2790	714		
	Calcium	ppm	ASTM D5185(m)		1241		
	Phosphorus	ppm	ASTM D5185(m)		782		
	Zinc	ppm	ASTM D5185(m)		913		
	Sulfur	ppm	ASTM D5185(m)		2243		
	Oxidation	Abs/.1mm	ASTM D7414*		17.8		
	Visc @ 40°C	cSt	ASTM D7279(m)		104		
	Visc @ 100°C	cSt	ASTM D7279(m)	15.4	14.0		
	Viscosity Index (VI)	Scale	ASTM D2270*	140	136		





ISO 17025:2017 Accredited Laboratory **Laboratory**: WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **Sample No.**: PN0006313 **Received**: 25 Jun 2024

 Diagnosed
 Unique Number
 : 5801471
 Diagnosed
 : 25 Jun 2024

 Diagnosed
 : 25 Jun 2024 - Wes Davis

Test Package: MOB 1 (Additional Tests: KV40, VI, Visual) To discuss this sample report, contact Customer Service at 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. Validity of results and interpretation are based on the sample and information as supplied.

POWER STATION INC. 1050 JAYSON COURT MISSISSAUGA, ON

CA L4W 2V5 Contact: Brett Kinkley Bkinkley@pwrstn.com

F: (905)565-8544

. (000)000 00