



# LIEBHERR

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**LIEBHERR L586 NOUNITLH0287857**  
Component  
**Diesel Engine**  
Fluid  
**SAE 5W30 (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LH0287857</b>	---	---
Sample Date		Client Info		<b>14 Jun 2024</b>	---	---
Machine Age	hrs	Client Info		<b>0</b>	---	---
Oil Age	hrs	Client Info		<b>0</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>N/A</b>	---	---
Filter Changed		Client Info		<b>N/A</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>100	<b>4</b>	---	---
Chromium	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	---	---
Nickel	ppm	ASTM D5185(m)	>5	<b>&lt;1</b>	---	---
Titanium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Silver	ppm	ASTM D5185(m)	>3	<b>0</b>	---	---
Aluminum	ppm	ASTM D5185(m)	>15	<b>2</b>	---	---
Lead	ppm	ASTM D5185(m)	>30	<b>0</b>	---	---
Copper	ppm	ASTM D5185(m)	>125	<b>1</b>	---	---
Tin	ppm	ASTM D5185(m)	>5	<b>0</b>	---	---
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	---	---

### CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>60	<b>7</b>	---	---
Potassium	ppm	ASTM D5185(m)	>20	<b>1</b>	---	---
Fuel		WC Method	>5	<b>&lt;1.0</b>	---	---
Water		WC Method	>0.2	<b>NEG</b>	---	---
Glycol		WC Method		<b>NEG</b>	---	---
Soot %	%	ASTM D7844*	>3	<b>0</b>	---	---
Nitration	Abs/cm	ASTM D7624*	>20	<b>8.8</b>	---	---
Sulfation	Abs/.1mm	ASTM D7415*	>30	<b>19.4</b>	---	---
Emulsified Water	scalar	Visual*	>0.2	<b>NEG</b>	---	---

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		<b>4</b>	---	---
Boron	ppm	ASTM D5185(m)		<b>38</b>	---	---
Barium	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Molybdenum	ppm	ASTM D5185(m)		<b>58</b>	---	---
Manganese	ppm	ASTM D5185(m)		<b>0</b>	---	---
Magnesium	ppm	ASTM D5185(m)		<b>1102</b>	---	---
Calcium	ppm	ASTM D5185(m)		<b>818</b>	---	---
Phosphorus	ppm	ASTM D5185(m)		<b>1002</b>	---	---
Zinc	ppm	ASTM D5185(m)		<b>1206</b>	---	---
Sulfur	ppm	ASTM D5185(m)		<b>2783</b>	---	---
Oxidation	Abs/.1mm	ASTM D7414*	>25	<b>18.3</b>	---	---
Visc @ 40°C	cSt	ASTM D7279(m)	60.0	<b>68.9</b>	---	---
Visc @ 100°C	cSt	ASTM D7279(m)	11.0	<b>11.6</b>	---	---
Viscosity Index (VI)	Scale	ASTM D2270*	177	<b>163</b>	---	---



**Laboratory** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**Sample No.** : LH0287857 **Received** : 28 Jun 2024  
**Lab Number** : 02644502 **Tested** : 02 Jul 2024  
**Unique Number** : 5802041 **Diagnosed** : 02 Jul 2024 - Kevin Marson  
**Test Package** : MOB 1 ( Additional Tests: KV40, VI )

**Quality Concrete Inc.**  
 35 Lafarge Lane  
 Folly Lake, NS  
 CA B0M 1M0  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-268-2131.  
 Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.  
 Validity of results and interpretation are based on the sample and information as supplied.

T:  
 F: