



Machine Id
13180
Component
Front Diesel Engine
Fluid
CASTROL HYPURON ADVANCED FORMULA (40 LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		PC	PC0071327	PC0071334
Sample Date		Client Info		04 Jul 2024	02 Jul 2024	05 Mar 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185(m)	>120	27	10	25
Chromium	ppm	ASTM D5185(m)	>20	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	<1	<1	<1
Titanium	ppm	ASTM D5185(m)	>2	0	0	0
Silver	ppm	ASTM D5185(m)	>2	<1	0	0
Aluminum	ppm	ASTM D5185(m)	>20	2	2	3
Lead	ppm	ASTM D5185(m)	>40	1	<1	2
Copper	ppm	ASTM D5185(m)	>330	12	2	10
Tin	ppm	ASTM D5185(m)	>15	0	0	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185(m)	>25	4	3	4
Potassium	ppm	ASTM D5185(m)	>20	2	6	3
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	0.0	NEG
Soot %	%	ASTM D7844*	>4	0.2	0.1	0.2
Nitration	Abs/cm	ASTM D7624*	>20	8.7	9.5	8.7
Sulfation	Abs/.1mm	ASTM D7415*	>30	19.9	20.5	20.0
Emulsified Water	scalar	Visual*	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		8	11	8
Boron	ppm	ASTM D5185(m)		8	4	3
Barium	ppm	ASTM D5185(m)		<1	0	<1
Molybdenum	ppm	ASTM D5185(m)		59	58	60
Manganese	ppm	ASTM D5185(m)		<1	<1	<1
Magnesium	ppm	ASTM D5185(m)		916	924	968
Calcium	ppm	ASTM D5185(m)		1033	1040	1067
Phosphorus	ppm	ASTM D5185(m)		954	944	999
Zinc	ppm	ASTM D5185(m)		1162	1163	1176
Sulfur	ppm	ASTM D5185(m)		2308	2369	2505
Oxidation	Abs/.1mm	ASTM D7414*	>25	16.4	18.1	17.0
Visc @ 40°C	cSt	ASTM D7279(m)	82.7	70.6	74.2	72.6
Visc @ 100°C	cSt	ASTM D7279(m)	12.1	10.8	11.1	11.1
Viscosity Index (VI)	Scale	ASTM D2270*	142	142	139	143



Laboratory : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
Sample No. : PC **Received** : 05 Jul 2024
Lab Number : 02645778 **Tested** : 05 Jul 2024
Unique Number : 5803317 **Diagnosed** : 05 Jul 2024 - Kevin Marson
Test Package : MOB 1 (Additional Tests: KV40, VI)

Wasteco
 161 Bridgeland Ave.
 Toronto, ON
 CA M6A 1Z1
 Contact: Steve Andrade
 sandrade@wasteco.com
 T: (416)787-5000
 F: (416)787-6210

To discuss this sample report, contact Customer Service at 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 Validity of results and interpretation are based on the sample and information as supplied.