

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area

Store 2 - Beaver [56604]

JOHN DEERE 450J 1T0450JXVCD228725

Transmission

JOHN DEERE TORQ GARD 10W30 (11 GAL)

JOHN DEERE TORQ GARD 10	W30 (11 GAI	<u>L)</u>					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LECP170619		
	Sample Date		Client Info		22 Dec 2016		
	Machine Age	hrs	Client Info		504		
	Oil Age	hrs	Client Info		504		
	Filter Age	hrs	Client Info		504		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD							
WEAR	PQ		ASTM D8184		17		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		4		
	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m	>9	4		
	Copper	ppm	ASTM D5185m		19		
	Tin	ppm	ASTM D5185m	>3	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Ciliaan		ACTM DE10Em	. 01	_		
CONTAININATION	Silicon	ppm	ASTM D5185m		5		
There is no indication of any contamination in the component.	Potassium	ppm	ASTM D5185m		4		
	Water			>0.075	NEG		
	Silt Debris	scalar	*Visual	NONE	NONE		
		scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML NEG		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>30	4		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		4		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		308		
	Calcium	ppm	ASTM D5185m		2609		
	Phosphorus	ppm	ASTM D5185m		1015		
	Zinc	ppm	ASTM D5185m		1374		
	Sulfur	ppm	ASTM D5185m		3693		
	Visc @ 40°C	cSt	ASTM D445		54.04		
Report Id: LESMAROH [WLISCAR] 04134241 (Generated: 05/08/2024 10:03:04) Rev: 1	Contact/Loca			BIETTA		ENDALL I	ESMAROH







Certificate L2367

Laboratory

Sample No.

: LECP170619 Lab Number : 04134241 Unique Number : 7652622

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 30 Dec 2016 **Tested** : 04 Jan 2017 Diagnosed

Test Package: MOB 1 (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: 04 Jan 2017 - Don Baldridge

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

LESLIE EQUIPMENT COMPANY

KendalLeanne@lec1.com T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (740)373-5570