

WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL

Store 8 - Pikeville [114485]

WGH0H235THAA01029

Component Hydraulic System

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TESSIMILITERIOR	Sample Number		Client Info		LEC0019531		
Resample at the next service interval to monitor.	Sample Date		Client Info		18 Mar 2021		
	Machine Age	hrs	Client Info		1165		
	Oil Age	hrs	Client Info		1165		
	Filter Age	hrs	Client Info		1165		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
A/F A D	 PQ		ACTM DO104		18		
VEAR		10 10 100	ASTM D8184	. 20			
All component wear rates are normal.	Iron	ppm	ASTM D5185m		3		
	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	10	0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		6		
	Tin	ppm	ASTM D5185m	>10	3		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal Yellow Metal	scalar scalar	*Visual *Visual	NONE	NONE NONE		
<u></u>	Tellow Metal	Scalai	Visuai		INONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		7		
There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.	Potassium	ppm	ASTM D5185m		5		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647		1437		
	Particles >6µm		ASTM D7647		415		
	Particles >14μm		ASTM D7647		33		
	Particles >21μm		ASTM D7647		8		
	Particles >38μm		ASTM D7647		0		
	Particles >71μm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		18/16/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The ANTI-out to accomplable for this first U.T.	Boron	ppm	ASTM D5185m		<1		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		22		
	Phosphorus	ppm	ASTM D5185m		260		
	Zinc	ppm	ASTM D5185m		317		
	Sulfur	ppm	ASTM D5185m		743		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.317		
	Visc @ 40°C	cSt	ASTM D445		47.0		





Certificate L2367

Laboratory Sample No. **Lab Number**

: LEC0019531 : 05210773 : 9434666 **Unique Number**

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : 23 Mar 2021 Recieved Diagnosed : 25 Mar 2021

Diagnostician : Don Baldridge Test Package : MOBCE (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

KendalLeanne@lec1.com

T: F: (740)373-5570