WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

[W00830]

JOHN DEERE 310SL 1T0310SLHKF363441

Component Transmission

,	JC	Ì	Н	N	ı)	E	:	E	I	3	E	:	ŀ	ď	Υ	٧.	.(G	ì	Δ	١	R)		H	ľ	Υ)	/	Τ	F	?	Æ	١	N	1	3	((-	-	_		C	ì	Α	L	_))	
				-		 -				-	-			-				_	-	-	_			 -	_	-			-	_			-	-			-	-			۰.	_	-	_			_			-	_

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0112664		
·	Sample Date		Client Info		21 Dec 2021		
	Machine Age	hrs	Client Info		513		
	Oil Age	hrs	Client Info		513		
	Filter Age	hrs	Client Info		513		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
VEAR	PQ		ASTM D8184	>100	31		
	Iron	ppm	ASTM D5185m	>61	36		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>20	10		
	Lead	ppm	ASTM D5185m	>9	1		
	Copper	ppm	ASTM D5185m	>100	23		
	Tin	ppm	ASTM D5185m	>3	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	0.11.		AOTA DE LOS	04			
CONTAMINATION	Silicon	ppm	ASTM D5185m		6		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m		2		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	VLITE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual	NORML NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NORML NEG		
<u></u>		Scalar	visuai	>0.075	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m	>30	7		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	17		
·	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	0	1		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m		91		
	Calcium	ppm	ASTM D5185m	3570	3515		
	Phosphorus	ppm		1290	1033		
	Zinc	ppm	ASTM D5185m	1640	1303		
	Sulfur	ppm	ASTM D5185m		3454		
	Visc @ 40°C	cSt	ASTM D445	57.0	41.4	J	





Report Id: JAMELI [WUSCAR] 05437233 (Generated: 02/29/2024 16:49:53) Rev: 1

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0112664 Lab Number : 05437233

Unique Number : 9801426

Received **Tested**

: 06 Jan 2022 : 06 Jan 2022 - Don Baldridge Diagnosed

: 05 Jan 2022

JRE - ELIZABETH CITY 129 KNOBBS CREEK DR ELIZABETH CITY, NC

US 27909 Contact: CHARLES PARKER

Test Package : MOBCE (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369. charles.parker@jamesriverequipment.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (252)333-2280

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: