

**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 

Store 4 - Fairmont

## JOHN DEERE 700K 1T0700KXHCE231102

Component Transmission

JOHN DEERE HYDRAU (18 GAL	_)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0026815		
	Sample Date		Client Info		17 Jan 2022		
	Machine Age	hrs	Client Info		1925		
	Oil Age	hrs	Client Info		1925		
	Filter Age	hrs	Client Info		1925		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>100	18		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>61	7		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>20	2		
	Lead	ppm	ASTM D5185m		4		
	Copper	ppm	ASTM D5185m		17		
	Tin	ppm	ASTM D5185m	>3	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	LIGHT		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION  There is no indication of any contamination in the fluid.	Silicon	ppm	ASTM D5185m	>21	14		
	Potassium	ppm	ASTM D5185m	>20	3		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>30	2		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m		6		
	Barium	ppm	ASTM D5185m		1		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		274		
	Calcium	ppm	ASTM D5185m		2463		
	Phosphorus	ppm	ASTM D5185m	727	1192		
	Zinc	ppm	ASTM D5185m		1314		
	Sulfur	ppm	ASTM D5185m		3871		
	Visc @ 40°C	cSt	ASTM D445	65	54.0		







Report Id: LESMAROH [WUSCAR] 05450398 (Generated: 02/23/2024 10:42:40) Rev: 1

Laboratory

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No.

: LEC0026815 Lab Number : 05450398

Unique Number : 9824593

**Tested** Diagnosed

Test Package : MOBCE ( Additional Tests: PQ )

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received

: 24 Jan 2022

: 25 Jan 2022

: 26 Jan 2022 - Jonathan Hester

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

T:

F: (740)373-5570