WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



JOHN DEERE 824K 1DW824KXVJF687635

Component **Brake**

JOHN DEERE HY-GARD HYDRAULIC/RANSMISSION (--- GAL)

JOHN DEERE HY-GARD HYDR	RAULIC/RAN	SMIS	SION (- GAL	<u>-)</u>		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0097916		
	Sample Date		Client Info		06 Apr 2022		
	Machine Age	hrs	Client Info		6564		
	Oil Age	hrs	Client Info		564		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD							
WEAR	PQ		ASTM D8184		12		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		14		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>5	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m	>10	4		
	Copper	ppm	ASTM D5185m	>150	5		
	Tin	ppm	ASTM D5185m	>5	<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	>400	3		
CONTAININATION	Potassium	ppm	ASTM D5185m		1		
There is no indication of any contamination in the fluid.	Water	ppm	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m		12		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		93		
	Calcium	ppm	ASTM D5185m		3552		
	Phosphorus	ppm	ASTM D5185m		1068		
	Zinc	ppm	ASTM D5185m		1308		
	Sulfur	ppm	ASTM D5185m		3087		
	Visc @ 40°C	cSt	ASTM D445	59	53.0		
Report Id: RWMFAY [WLISCAR] 05514473 (Generated: 05/28/2024 09:40:54) Rev: 1				Sub	mitted By: TI	CHNICIAN	ACCOLINIT.





Laboratory Sample No.

: JR0097916 Lab Number : 05514473

Unique Number : 9928752

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Diagnosed

: 08 Apr 2022 : 11 Apr 2022 : 11 Apr 2022 - Don Baldridge

JRE - HOPE MILLS/FAYETTEVILLE

5039 HWY 301 SOUTH HOPE MILLS, NC

US 28348 Contact: FAYETTEVILLE SHOP

Test Package : MOBCE (Additional Tests: PQ) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. stephen.mullis@jamesriverequipment.com;canastasio@wearcheck.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: