



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Area


## Store 4 - Fairmont [132817]

## JOHN DEERE 250GLC 1FF250GXLNF611863

Hydraulic System

HITACHI HYDRAULIC SUPER EX 46HN (63 GAL)

HITACHI HYDRAULIC SUPER E	X 46HN (63	GAL	) 				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		LEC0033038		
Resample at the next service interval to monitor.	Sample Date		Client Info		12 Oct 2022		
	Machine Age	hrs	Client Info		497		
	Oil Age	hrs	Client Info		497		
	Filter Age	hrs	Client Info		497		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>50	2		
	Iron	ppm	ASTM D5185m	>32	<1		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	70	<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>9	<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	70	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Ciliana		ACTM DE10Ess	4.4			
	Silicon	ppm	ASTM D5185m		1		
There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.	Potassium	ppm	ASTM D5185m		0		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647		4596		
	Particles >6µm		ASTM D7647		391		
	Particles >14µm		ASTM D7647		21		
	Particles >21µm		ASTM D7647		5		
	Particles >38µm		ASTM D7647		1		
	Particles >71μm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		19/16/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
<u></u>	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>21	1		
TI AND 11	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		0		
	Phosphorus	ppm	ASTM D5185m	827	509		
	Zinc	ppm	ASTM D5185m		23		
	Sulfur	ppm	ASTM D5185m	13	0		
	Guilai	le le					
	Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.14		







Certificate L2367

Laboratory Sample No. Lab Number

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0033038 : 05668104

Unique Number: 10177674

**Tested** Diagnosed

Test Package : CONST ( Additional Tests: PQ ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Received

KendalLeanne@lec1.com T:

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR.

Contact: LEANNE KENDALL

MARIETTA, OH

US 45750-9765

F: (740)373-5570

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: 18 Oct 2022 - Jonathan Hester

: 17 Oct 2022

: 18 Oct 2022