

WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL ATTENTION

Store 9 - Marietta

JOHN DEERE 35G 1FF035GXJMK293636

Right Propel Gearbox

| JOHN DEERE GL-5 80W90 (20 Oz) | | | | | | | |
|--|------------------|--------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | LEC0035586 | | |
| | Sample Date | | Client Info | | 20 Oct 2022 | | |
| | Machine Age | hrs | Client Info | | 255 | | |
| | Oil Age | hrs | Client Info | | 255 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | None | | |
| | Sample Status | | | | ATTENTION | | |
| WEAR | PQ | | ASTM D8184 | | 77 | | |
| All component wear rates are normal. | Iron | ppm | ASTM D5185m | >1250 | 163 | | |
| | Chromium | ppm | ASTM D5185m | | 3 | | |
| | Nickel | ppm | ASTM D5185m | | 0 | | |
| | Titanium | ppm | ASTM D5185m | | 1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | | 5 | | |
| | Lead | ppm | ASTM D5185m | | 0 | | |
| | Copper | ppm | ASTM D5185m | | 2 | | |
| | Tin | ppm | ASTM D5185m | | <1 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | White Metal | scalar | *Visual | NONE | MODER | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION There is no indication of any contamination in the oil. | Silicon | ppm | ASTM D5185m | | 18 | | |
| | Potassium | ppm | ASTM D5185m | >20 | <1 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 1 | | |
| The oil viscosity is lower than normal. This plus the additive levels indicates the addition of a different brand, or type of oil. Confirm oil type. | Boron | ppm | ASTM D5185m | | <u> </u> | | |
| | Barium | ppm | ASTM D5185m | | 35 | | |
| | Molybdenum | ppm | ASTM D5185m | | 17 | | |
| | Manganese | ppm | ASTM D5185m | | 3 | | |
| | Magnesium | ppm | ASTM D5185m | | 13 | | |
| | Calcium | ppm | ASTM D5185m | | 4009 | | |
| | Phosphorus | ppm | ASTM D5185m | | 609 | | |
| | Zinc | ppm | ASTM D5185m | | 719 | | |
| | Sulfur | ppm | ASTM D5185m | | 2968 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 94.3 | | |







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 05674601

: LEC0035586

Unique Number : 10189172

Diagnosed Test Package : CONST (Additional Tests: PQ)

Received

Tested

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: 24 Oct 2022

: 26 Oct 2022

: 26 Oct 2022 - Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

T:

F: (740)373-5570