



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 672G 6309 (S/N 1DW672GPADE656175)

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (7 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0134190	JR0031877	JR0017331
Sample Date		Client Info		08 Oct 2022	03 Jan 2020	22 Aug 2019
Machine Age	hrs	Client Info		3779	1954	1516
Oil Age	hrs	Client Info		500	500	0
Filter Age	hrs	Client Info		500	500	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	55	24	38
Chromium	ppm	ASTM D5185m	>11	1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	2	3
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>31	6	6	6
Lead	ppm	ASTM D5185m	>26	<1	0	0
Copper	ppm	ASTM D5185m	>26	5	12	▲ 49
Tin	ppm	ASTM D5185m	>4	<1	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	6	5	3
Potassium	ppm	ASTM D5185m	>20	11	2	4
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.8	0.3	0.4
Nitration	Abs/cm	*ASTM D7624	>20	11.1	8.1	9.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.7	20.9	22.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	0	3	5
Boron	ppm	ASTM D5185m		125	210	154
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		167	243	218
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		594	793	720
Calcium	ppm	ASTM D5185m		1476	1393	1262
Phosphorus	ppm	ASTM D5185m		810	844	782
Zinc	ppm	ASTM D5185m		994	978	889
Sulfur	ppm	ASTM D5185m		3141	3642	2425
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.6	15.6	17.4
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.0	8.9	8.9
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	14.1	14.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0134190 **Received** : 04 Nov 2022
Lab Number : 05685033 **Tested** : 07 Nov 2022
Unique Number : 10204605 **Diagnosed** : 08 Nov 2022 - Angela Borella
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CK CONTRACTING
 124-1 WOODING PL
 KINGS MOUNTAIN, NC
 US 28086
 Contact: TAM WRIGHT
 twright@ckcdllc.com
 T: (704)730-9948
 F: (704)730-9975