



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
{unassigned}
Machine Id
JOHN DEERE 250G 1FF250GXLLF611603
Component
Diesel Engine
Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (5 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0037032	LEC0029555	LEC0018483
Sample Date		Client Info		23 Nov 2022	20 May 2022	24 Nov 2021
Machine Age	hrs	Client Info		1515	964	478
Oil Age	hrs	Client Info		551	486	57
Filter Age	hrs	Client Info		551	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	35	22	5
Chromium	ppm	ASTM D5185m	>11	1	1	<1
Nickel	ppm	ASTM D5185m	>5	3	10	6
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>31	4	4	4
Lead	ppm	ASTM D5185m	>26	<1	<1	0
Copper	ppm	ASTM D5185m	>26	11	13	11
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	9	6	5
Potassium	ppm	ASTM D5185m	>20	3	1	7
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.4	0.1
Nitration	Abs/cm	*ASTM D7624	>20	12.0	9.3	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	28.3	23.2	20.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	3	3	2
Boron	ppm	ASTM D5185m		119	182	194
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		258	251	199
Manganese	ppm	ASTM D5185m		1	1	<1
Magnesium	ppm	ASTM D5185m		773	898	833
Calcium	ppm	ASTM D5185m		1608	1558	1626
Phosphorus	ppm	ASTM D5185m		882	923	894
Zinc	ppm	ASTM D5185m		1106	1116	1018
Sulfur	ppm	ASTM D5185m		2720	2732	3601
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.6	18.3	15
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	9.0	8.0	10.6
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	14.1	14.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0037032 **Received** : 28 Nov 2022
Lab Number : 05703330 **Diagnosed** : 29 Nov 2022
Unique Number : 10232904 **Diagnostician** : Angela Borella
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY
 105 TENNIS CENTER DR.
 MARIETTA, OH
 US 45750-9765
 Contact: LEANNE KENDALL
 KendalLeanne@lec1.com
 T:
 F: (740)373-5570