
WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id **HAMILTON**

Component Starboard Genset

	T4	11014	MadleI	Library (Alle	O	I Bake or of	111-4
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		MW05774574 07 Feb 2023		
	Sample Date Machine Age	bro	Client Info				
	•	hrs			13003		
	Oil Age Filter Age	hrs	Client Info		499 0		
	Oil Changed	hrs	Client Info		N/A		
	_		Client Info		N/A N/A		
	Filter Changed		Client Into				
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>25	9		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>5	0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		2		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Fuel		WC Method	>4.0	<1.0		
	Water		WC Method	>0.1	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	9.1		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		66		
oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		21		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		621		
	Calcium	ppm	ASTM D5185m		1578		
	Phosphorus	ppm	ASTM D5185m		710		
	Zinc	ppm	ASTM D5185m		868		
	Sulfur	ppm	ASTM D5185m		2993		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	17.8		
	Base Number (BN)				8.3		
	Visc @ 100°C	cSt	ASTM D445		12.8		







Certificate L2367

Laboratory

Sample No.

: MW05774574 Lab Number : 05774574 Unique Number : 10349191 Test Package : MAR 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 23 Feb 2023 : 24 Feb 2023 **Tested**

Diagnosed

: 24 Feb 2023 - Don Baldridge

PO BOX 391 LEMONT, IL US 60439 Contact: RHETT DANIEL rdaniel@imtowing.com

ILLINOIS MARINE TOWING

T: (630)280-4926 F: (630)739-2041

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)