
**WEAR** CONTAMINATION **FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

Machine Id

090928B

Component Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TEOOMMENDATION	Sample Number	JOIVI	Client Info	EIIIII//NOT	WC0789302		
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Date		Client Info		07 Mar 2023		
	Machine Age	hrs	Client Info		1030		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAD.	lron		ACTM DE10Em	. 100	E		
VEAR	Iron Chromium	ppm	ASTM D5185m ASTM D5185m		5 <1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	74	<1		
	Silver	ppm		>3	0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	7.0	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		5		
There is no indication of any contamination in the cil	Potassium	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	7.5		
	Sulfation	Abs/.1mm	*ASTM D7415		17.2		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual *Visual	NORML	NORML		
	Emulsified Water	scalar scalar	*Visual	NORML >0.2	NORML NEG		
			VIOUGI				
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The DN constitution that the section of table all a fletter are a few at the	Boron	ppm	ASTM D5185m		34		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		6		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		43		
	Calcium	ppm	ASTM D5185m		2300		
	Phosphorus	ppm	ASTM D5185m		914		
	Zinc	ppm	ASTM D5185m		1158		
	Sulfur	ppm	ASTM D5185m	0.5	3999		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	10.6		
	Base Number (BN)		ASTM D2896		9.31		
	Visc @ 40°C	cSt	ASTM D445		96.6		
	Visc @ 100°C Viscosity Index (VI)	cSt Scale	ASTM D445 ASTM D2270		13.5 140		





Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** 

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0789302 : 05796716 : 10386400

Recieved : 20 Mar 2023 : 23 Mar 2023 Diagnosed Diagnostician : Wes Davis

Test Package : MOB 2 ( Additional Tests: KV40, VI ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**HIAB USA - Plainfield** 702 COLUMBIA RD PLAINFIELD, IN US 46168-7595 Contact: CHUCK WISHARD chuck.wishard@hiab.com T: (240)625-0045