



WEAR	ABNORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	ATTENTION



Area

[F&B CONCRETE]

Machine Id

JOHN DEERE 1T0325GKJNJ421438

Component

Diesel Engine

Fluid

JOHN DEERE ENGINE OIL PLUS 50 II 0W40 (--- GAL)

RECOMMENDATION

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0174769	---	---
Sample Date		Client Info		16 May 2023	---	---
Machine Age	hrs	Client Info		455	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				ABNORMAL	---	---

WEAR

The copper level is abnormal. In the absence of other significant wear metals, suspect copper due to sources other than wear (i.e. cooling core). All other metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>51	48	---	---
Chromium	ppm	ASTM D5185m	>11	1	---	---
Nickel	ppm	ASTM D5185m	>5	<1	---	---
Titanium	ppm	ASTM D5185m		0	---	---
Silver	ppm	ASTM D5185m	>3	0	---	---
Aluminum	ppm	ASTM D5185m	>31	14	---	---
Lead	ppm	ASTM D5185m	>26	2	---	---
Copper	ppm	ASTM D5185m	>26	▲ 100	---	---
Tin	ppm	ASTM D5185m	>4	1	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION










Elemental level of silicon (Si) above normal indicating ingress of seal material. Light fuel dilution occurring.

Silicon	ppm	ASTM D5185m	>22	▲ 42	---	---
Potassium	ppm	ASTM D5185m	>20	0	---	---
Fuel	%	ASTM D3524	>5	▲ 2.6	---	---
Water		WC Method	>0.21	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>3	0.6	---	---
Nitration	Abs/cm	*ASTM D7624	>20	10.6	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.9	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.21	NEG	---	---

FLUID CONDITION

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil.

Sodium	ppm	ASTM D5185m	>31	13	---	---
Boron	ppm	ASTM D5185m		179	---	---
Barium	ppm	ASTM D5185m		0	---	---
Molybdenum	ppm	ASTM D5185m		258	---	---
Manganese	ppm	ASTM D5185m		1	---	---
Magnesium	ppm	ASTM D5185m		694	---	---
Calcium	ppm	ASTM D5185m		1850	---	---
Phosphorus	ppm	ASTM D5185m		839	---	---
Zinc	ppm	ASTM D5185m		1058	---	---
Sulfur	ppm	ASTM D5185m		3448	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.8	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	7.8	---	---
Visc @ 100°C	cSt	ASTM D445	14	● 11.7	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0174769 **Received** : 17 May 2023
Lab Number : 05850122 **Tested** : 19 May 2023
Unique Number : 10479477 **Diagnosed** : 22 May 2023 - Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, PercentFuel, TBN)

ALLSITE CONTRACTING
 11128 INDUSTRIAL RD
 MANASSAS, VA
 US 20109
 Contact: DAVE PARKER
 dave.parker@allsiteco.com
 T: (703)361-2499
 F: (703)361-6169

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)