



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
924034-260283

Component
Diesel Engine

Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0082693	GFL0074689	GFL0064646
Sample Date		Client Info		26 May 2023	24 Mar 2023	06 Feb 2023
Machine Age	hrs	Client Info		75087	58726	58081
Oil Age	hrs	Client Info		75087	78529	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	35	18	6
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		2	2	21
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>20	3	2	<1
Lead	ppm	ASTM D5185m	>40	2	<1	<1
Copper	ppm	ASTM D5185m	>330	6	4	16
Tin	ppm	ASTM D5185m	>15	1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	14	12	▲ 25
Potassium	ppm	ASTM D5185m	>20	2	1	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.3	6.6	5.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.6	18.0	14.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	3	6
Boron	ppm	ASTM D5185m	0	3	4	0
Barium	ppm	ASTM D5185m	0	0	0	5
Molybdenum	ppm	ASTM D5185m	60	60	61	41
Manganese	ppm	ASTM D5185m	0	2	1	2
Magnesium	ppm	ASTM D5185m	1010	974	982	805
Calcium	ppm	ASTM D5185m	1070	1045	1075	1129
Phosphorus	ppm	ASTM D5185m	1150	1036	1040	953
Zinc	ppm	ASTM D5185m	1270	1274	1300	1141
Sulfur	ppm	ASTM D5185m	2060	3691	3936	3239
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.3	13.7	11.1
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.4	9.1	9.7
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.3	13.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0082693 **Received** : 31 May 2023
Lab Number : 05861260 **Diagnosed** : 01 Jun 2023
Unique Number : 10495725 **Diagnostician** : Wes Davis
Test Package : FLEET

GFL Environmental - 814 - Little Rock Hauling
 4005 Hwy 161 N.
 Little Rock, AR
 US 72117
 Contact: Brad Koenig
 bkoenig@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: