



Store 2 - Beaver [RO#139855] JOHN DEERE 550K 1T0550KKTNF432092 Left Final Drive

JOHN DEERE HY-GARD HYD/TRANS (2 GAL)

					~		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0037639		
	Sample Date		Client Info		06 Jun 2023		
	Machine Age	hrs	Client Info		583		
	Oil Age	hrs	Client Info		583		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	27		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>500	54		
	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	<1		
	Lead	ppm	ASTM D5185m	>25	0		
	Copper	ppm	ASTM D5185m	>50	<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		10		
	Potassium	ppm	ASTM D5185m		<1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual	NORML	NORML		
		scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	3		
The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m	6	0		
	Barium	ppm	ASTM D5185m	0	0		
	Molybdenum	ppm	ASTM D5185m	0	<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	145	99		
	Calcium	ppm	ASTM D5185m	3570	3461		
	Phosphorus	ppm	ASTM D5185m	1290	1018		
	Zinc	ppm	ASTM D5185m	1640	1240		
	Sulfur	ppm	ASTM D5185m		4116		
	Vice @ 40°C	oC+	ACTM D445	57.0	51.6		


Visc @ 40°C


cSt


Submitted By: STORE 2 - BEAVER - CASEY TONEY

51.6

ASTM D445 57.0







Submitted By: STORE 2 - BEAVER - CASEY TONEY Page 2 of 2