WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

{UNASSIGNED}

JOHN DEERE 200G 8001859 (S/N 1Ff210gxplf528983)

Component Bogie/Center Swing Drive

{not provided} (55)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0173754		
	Sample Date		Client Info		14 Jun 2023		
	Machine Age	hrs	Client Info		1516		
	Oil Age	hrs	Client Info		1516		
	Filter Age	hrs	Client Info		1516		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		28		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>151	45		
	Chromium	ppm	ASTM D5185m	>11	<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	MODER		
<u></u>	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML NEG		
	Emulsified Water	Sudiai	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		151		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		20		
	Phosphorus Zinc	ppm	ASTM D5185m ASTM D5185m		740 2		
	Sulfur	ppm	ASTM D5185m		20931		
	Visc @ 40°C	cSt	ASTM D3163III		141		
Report Id: RWMNEW IWI ISCARI 05875887 (Generated: 01/10/2024 15:24:00) Rev. 1	¥100 @ +0 O	001	, to the DTTO				REBNI SHOP







Certificate L2367

Laboratory Sample No. Lab Number **Unique Number**

: JR0173754

: 05875887 : 10520990 Test Package : CONST (Additional Tests: PQ)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 16 Jun 2023 Diagnosed Diagnostician : Jonathan Hester

: 20 Jun 2023

JRE - NEW BERN 3816 MARTIN LUTHER KING BLVD NEW BERN, NC US 28562

Contact: NEW BERN SHOP nick.etherdridge@jamesriverequipment.com;canastasio@wearcheckusa.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: