



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
CHA
Component
Starboard Main Engine
Fluid
CHEVRON DELO 400 XLE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW05877875	MW05843062	MW05823766
Sample Date		Client Info		19 Jun 2023	09 May 2023	18 Apr 2023
Machine Age	hrs	Client Info		52222	51354	50370
Oil Age	hrs	Client Info		1848	984	3540
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>75	8	1	9
Chromium	ppm	ASTM D5185m	>8	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>3	<1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	2	5	0
Lead	ppm	ASTM D5185m	>18	0	0	0
Copper	ppm	ASTM D5185m	>80	<1	0	<1
Tin	ppm	ASTM D5185m	>14	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	8	4	7
Potassium	ppm	ASTM D5185m	>20	1	1	2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.4	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.4	5.7	6.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.8	21.5	21.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	1	<1	2
Boron	ppm	ASTM D5185m		447	323	340
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		139	101	115
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		656	539	604
Calcium	ppm	ASTM D5185m		1933	1548	1730
Phosphorus	ppm	ASTM D5185m	760	1145	869	1022
Zinc	ppm	ASTM D5185m	830	1335	1063	1211
Sulfur	ppm	ASTM D5185m	2770	3915	3147	3586
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0	14.9	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.7	8.4	8.5	8.3
Visc @ 100°C	cSt	ASTM D445	14.9	13.3	13.3	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW05877875
Lab Number : 05877875
Unique Number : 10522978
Test Package : MAR 2

Received : 20 Jun 2023
Tested : 21 Jun 2023
Diagnosed : 21 Jun 2023 - Sean Felton

ILLINOIS MARINE TOWING
 PO BOX 391
 LEMONT, IL
 US 60439
 Contact: RHETT DANIEL
 rdaniel@imtowing.com
 T: (630)280-4926
 F: (630)739-2041

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)