



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
ALEX G
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 MULTIGRADE 15W40 (4 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0533224	WC0533221	WC0759372
Sample Date		Client Info		10 Jun 2023	12 May 2023	24 Jan 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		500	0	500
Filter Age	hrs	Client Info		500	0	500
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	2	4	4
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m	>2	8	10	3
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	2
Lead	ppm	ASTM D5185m	>40	0	<1	3
Copper	ppm	ASTM D5185m	>330	0	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	4	4
Potassium	ppm	ASTM D5185m	>20	2	3	<1
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	0.1	0.1	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.9	8.6	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.7	19.8	22.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	<1	2
Boron	ppm	ASTM D5185m	151	139	136	283
Barium	ppm	ASTM D5185m	0.4	0	0	0
Molybdenum	ppm	ASTM D5185m	250	49	62	99
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	0	689	665	645
Calcium	ppm	ASTM D5185m	2046	1424	1482	1535
Phosphorus	ppm	ASTM D5185m	1043	686	705	667
Zinc	ppm	ASTM D5185m	943	812	838	805
Sulfur	ppm	ASTM D5185m	5012	3462	3009	2977
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.8	15.1	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	12.5	9.1	8.5	9.0
Visc @ 100°C	cSt	ASTM D445	14.4	14.1	13.1	12.9



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0533224 **Received** : 21 Jun 2023
Lab Number : 05880085 **Diagnosed** : 23 Jun 2023
Unique Number : 10525188 **Diagnostician** : Don Baldrige
Test Package : MOB1+

ASSOCIATED TERMINALS - CRANE

CONVENT, LA
 US 70723
 Contact: LONNY BECNEL
 lbecnel@associatedterminals.com
 T: (225)562-3919
 F: (225)562-3515

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)