



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**811046**

Component  
**Diesel Engine**

Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0082634</b>	GFL0082625	GFL0074748
Sample Date		Client Info		<b>19 Jun 2023</b>	30 May 2023	03 May 2023
Machine Age	hrs	Client Info		<b>4822</b>	4670	4531
Oil Age	hrs	Client Info		<b>152</b>	0	52
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>15</b>	10	56
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	0	2
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	0	<1
Titanium	ppm	ASTM D5185m		<b>0</b>	0	0
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>12</b>	9	25
Lead	ppm	ASTM D5185m	>40	<b>0</b>	0	0
Copper	ppm	ASTM D5185m	>330	<b>1</b>	<1	2
Tin	ppm	ASTM D5185m	>15	<b>0</b>	0	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>8</b>	7	13
Potassium	ppm	ASTM D5185m	>20	<b>27</b>	23	40
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>0.5</b>	0.4	1.1
Nitration	Abs/cm	*ASTM D7624	>20	<b>7.0</b>	6.0	9.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>19.4</b>	18.6	19.1
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>2</b>	4	4
Boron	ppm	ASTM D5185m	0	<b>10</b>	14	1
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>88</b>	81	57
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	1
Magnesium	ppm	ASTM D5185m	1010	<b>874</b>	917	970
Calcium	ppm	ASTM D5185m	1070	<b>1086</b>	1075	1040
Phosphorus	ppm	ASTM D5185m	1150	<b>964</b>	966	1004
Zinc	ppm	ASTM D5185m	1270	<b>1196</b>	1186	1275
Sulfur	ppm	ASTM D5185m	2060	<b>3426</b>	3693	3523
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>15.5</b>	13.7	15.8
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.0</b>	8.7	6.7
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.8</b>	13.9	13.5



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0082634 **Received** : 23 Jun 2023  
**Lab Number** : 05882524 **Diagnosed** : 27 Jun 2023  
**Unique Number** : 10533007 **Diagnostician** : Wes Davis  
**Test Package** : FLEET

**GFL Environmental - 814 - Little Rock Hauling**  
 4005 Hwy 161 N.  
 Little Rock, AR  
 US 72117  
 Contact: Brad Koenig  
 bkoenig@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: